Notebook, N-Undated.16

INDEX TO SECTION I AND II

4421-19	4199 - 97
4426-24	4213 - 09
4461-58	4266 - 64
4465-63	4356 - 54
4470-68	4361 - 59
4483 - 80	4387 - 85
4485-83	4391 - 89
4532-21	4416 - 99
4526-24	4406 - 04
4531-29	4411 - 14
4536-34	4459 - 57
4541-39	4492 - 90
4603-01	4914 - 11
4627-25	4921 - 19
4632-31	4927 - 25
4638-34	4935 - 34
4664-60	4945 - 46
4666-65	4958 - 57
4727-20	4963 - 60
4734-4728	4968 - 64
4734-4732	4973 - 70
4736-4734	4977 - 74
4767-65	5013 - 08
4777-75	4983 - 84
4804-02	5030 - 28
4809-07	5035 - 32
4816-12	5041 - 38
4840-38	5045 - 43
4838-11	5053 - 49
4838-4833	5057 - 54
4859-57	5062 - 59
4863-60	5065 - 64
4875-72	5092 - 90
4882-80	5097 - 93
4900-4836	5100 - 5098
4903-01	5177 - 15
4906-07	5119 - 17
4906C-A	5129 - 27
4906F-D	5134 - 32
4906C-A	
4912-10	

.00-00-00.16

SHERWOOD PRESS
PRINTERS
PHOENIX, ARIZ.

Note

Endurance cells selected from Work book #1 follows after endurance cells group #4909-07

Calipers

	Original	After 1st Run	Before Endurance	After Endurance
4421	93-103-103	102-107	103-106	
20	88-100-100	97-102	100-102	
19	92-100-103	101-105	103-107	

Section I

4421 }
4420 } Group 5 Ni Recessed Profs Chgd on 33⅓
4419 } 1150 Fahr 15 H. against CP Ni 515 @ 100 rate

then on 21½ rchg 15 H 200 div 100 use next irons
Cathodes –

4421	615	479	537	460	530	582	530	531	538
20	620	474	513	459	533	537	520	526	532
19	612	467	529	453	529	532	521	523	530

Endurance

	62	64	65	116	117	168	169	220	221
4421	530	522	518	538	500	467	483	410	407
20	533	508	515	525	488	465	455	417	468
19	533	512	517	517	493	460	452	416	402

	272	273	324	325	476	477	528	529		580
4421	386	361	332	319	180	169	147	142		144
20	395	377	340	324	222	213	163	137		143
19	390	367	345	340	183	171	150	137		100

Finish Grinding

	68
4421	100
20	107
19	95

Calipers

	Original	after 1st Run	Before Endurance	After Endurance
4426	92-102-103	100-104	101-103	
25	92-101-103	100-104	103-104	
24	92-101-103	99-105	103-103	

Section I

4426 Group 5 Mi Rated perfs chgd 21%
4425 15 hr 100 rate Temp 150,7. Then chg 21%
4424 Cont. 15 hr absch 100 use new calibrated irons

	1	2	3	4	5	6	7	8	9	
4426	583	461	520	442	518	522	517	517	520	
25	578	443	520	440	518	523	504	517	517	
24	587	460	530	455	527	532	521	518	523	

Endurance

	0	63	64	116	117	168	169	220	221
4426	530	500	483	517	483	465	452	432	412
25	543	504	500	522	487	467	457	400	400
24	543	512	497	533	498	477	467	432	412

	272-273	324	325	376	377	428	429	480		480
4426	412	393	392	377	241	217	215	212	Body Hot	190
25	393	375	342	343	217	200	217	217		182
24	407	383	351	357	217	200	163	167		103

	681										
4426	197										
25	190										
24	117										

Calipers

	Original	after 1st Run	Before Endurance	After Endurance
4461	87-98-99	103-103	105-104	
59	91-100-104	106-107	109-107	
58	88-100-99	105-105	109-105	

Section I

4461. 5 Reg Ni Chgd 15 h 33⅓ 150 Fahr
4459 100 rate 80H Containing 3 grammes of
4458 Metallic Aluminium Then put in 21½ H
Chg 200 rate 15 h dis 100

4461	292	357	271	373	377	382	373	378	
59	305	63	306	417	425	429	425	428	
58	315	400	316	416	419	427	421	418	

Endurance

	60	62	63	115	116	167	168	219	220
4461	377	367	367	365	333	300	303	233	242
59	50	50	432	448	430	370	363	347	50
58	433	432	432	391	395	333	338	277	280

	271	272	323	324	375	476	577	578		679
4461	233	233	167	50	94	82	73	95	100 Hours	77
59	340	337	273	289	163	145	123	133		103
58	272	271	233	208	113	110	87	107		90

	680									
4461	87									
59	119									
58	113									

Calipers

	Original	after 1st Run	Before Endurance	After Endurance
44465	94-99-101	92-98	96-97	
64	91-95-104	100-108		
63	89-97-104	97-103		

Section I

4465 5 Ni put in 21% chyd 200 rate 15 h.
64 dischg 100 KOH. Containing 3 grams
63 Cyanide Potassium - R29 index to 62 changed
24 hours at 200 before putting in cell with Nickel.

4465	37	493	537	513	532	525	507	505	493
64	0	550	565	540	527	400	533	527	550
63	33	508	545	518	540	532	543	532	510

513	538	518	522	523	532
528	523	512	519	515	527
528	545	532	530	SC	530

Endurance

	67	69	70	122	138	144	175	226	227
4465	567	533	540	563	540	518	520	487	497
64	578	540	533	586	528	517	508	486	SC
63	SC	600	555	577	548	517	523	498	493

	278	279	330	331	482	483	584	585	9	686
4465	478	477	455	467	394	387	498	300	Pressed 21% KOH 24 hrs	223
64	487	SC	455	463	SC	374	348	SC		347
63	500	490	467	473	400	393	343	345		331

	687
4465	237
64	305
63	298

Calipers

	Original	after 1st Run	Before Endurance	After Endurance
4470	93-103-103	102-105	106-106	
69	92-101-104	100-108	105-103	
68	87-97-100	95-102	100-104	

Section I

4470	5 Ni put in 21/1 Chg 200 dis 100 15 h
69	KOH Containing 3 grms Hyposulphite Soda
68	Reg runs to 62 chgd 24 hours before putting in cell with Ni

4470	442	515	553	518	525	517	533	512	527	517
69	420	513	533	510	X	X	SC	SC	SC	SC
68	436	503	525	507	513	504	533	507	522	517

516	527	518
SC	502	514
504	525	517

Endurance

	65	67	68	120	121	172	173	224	225
4470	582	533	528	547	523	540	500	478	467
69	533	523	523	553	523	515	500	490	475
68	565	533	523	553	SC	527	523	475	495

	276	277	328	329	480	481	532	583		684
4470	475	456	442	452	360	332	441	253	Probably Short Circuited	269
69	490	472	465	475	412	393	338	350		322
68	456	487	407	458	327	307	223	230		242

	685
4470	250
69	307
68	243

Caliper

	Original	after 1st Run	Before Endurance	After Endurance
4482	90 - 99 - 101		103 - 104	
81	91 - 97 - 100		103 - 106	
80	88 - 100 - 102		102 - 107	

Section I

4482 — 5 Ni chgd 200 rate .15 to dis 100 in 21%
81 — which has been boiled with filter paper
80 — runs to 62 chgd 24 hours before ni put with it.

4482	442	532	533	527	527	511	512	513	497	513	500
81	432	508	532	517	513	510	512	511	500	512	505
80	447	507	528	510	517	497	508	500	493	495	497

Endurance

	63	65	66	118	119	120	121	222	223
4482	565	533	527	558	522	C.C.	477	478	483
81	575	515	527	565	523	528	510	485	480
80	555	530	520	545	516	500	495	467	465

	274	275	326	327	478	479	580	581			693
4482	467	456	447	448	387	370	333	337			237
81	489	467	457	467	389	371	347	357			354
80	465	454	439	448	377	355	334	333			193

Annealed

	693										
4482	345										
81	378										
80	138										

Caliper

	original	after 1st Run	Before Endurance	after Endurance
4485	89-100-104		106-105	
84	90-100-103		109-106	
83	89-100-102		112-108	

Section I

4485 Dup of 4482 next page back Except
84 ROH has in addition 2 grams freshly
" 83 precip Mecuric Oxide put in -

4485	448	463	530	512	523	510	510	507	492	498	495
84	456	520	530	515	522	510	512	510	497	502	503
83	457	512	530	514	522	510	513	510	497	497	498

Endurance

	63	65	66	118	119	170	171	222	223
4485	567	533	525	557	527	515	500	475	467
84	573	530	502	568	527	535	510	498	497
83	567	535	523	597	515	500	492	462	464

	274	275	326	327	428	429	580	581	
4485	473	455	442	452	380	360	344	345	Pump Test
84	500	476	467	480	412	392	370	390	ROH Wet
83	463	445	433	440	371	344	317	317	

	682	683							
4485	250	263							
84	346	325							
83	260	263							

Calipers

	Original	after 1st Run	Before Endurance	after Endurance
4523	90-95-102	97-86	103-100	
22	92-102-104	98-100	102-103	
21	89-100-103	97-104	103-105	

	665	666
4523	269	277
22	205	200
21	308	272

Section I

4523	5 Ni Cupoplated with Iron (thinly)
22	Chg 21 1/2 h 200 dis 100
" 21	

	1	2	3	4	5	6	7	8	
4523	500	508	494	488	495	487	485	490	481
22	500	506	495	490	493	487	483	487	475
21	495	506	495	490	492	488	486	487	477

	475	488	X	482	484
	467	488	483	484	484
	467	488	483	483	484

Endurance

	65	67	68	121	122	173	174	225	226
4523	533	515	498	528	484	483	458	443	433
22	525	500	498	520	477	480	451	433	412
21	520	500	498	523	481	483	455	433	430

	277	278	329	330	481	482	583	584
4523	458	438	420	430	339	315	245	245
22	447	417	405	400	287	249	180	177
21	452	427	410	408	312	284	215	213

Caliper

	Original	after 1st. Run	Before Endurance	after Endurance
4526	90 - 101 - 103	98 - 103	102 - 104	
25	90 - 102 - 103	99 - 102	101 - 104	
24	89 - 102 - 104	97 - 103	103 - 104	

Section I

4526	3 mi cups plated very thin with Silver
25	21% clg 15 h 200 clo 100
24	

4526	512	524	524	527	508	525	510	507	491	493	500
25	173	516	525	527	512	532	516	508	488	500	500
24	521	524	506	527	500	525	512	507	500	497	501

Endurance

	63	65	66	118	119	170	171	222	223
4526	533	515	500	500	500	493	492	465	460
25	575	527	522	552	510	510	492	477	467
24	545	527	497	548	501	505	492	475	463

	274	275	326	327	478	479	580	581		682
4526	453	437	430	433	354	337	302	310		222
25	477	450	447	440	354	339	287	290		238
24	467	452	447	447	380	359	345	345		264

	683									
4526	225									
25	233									
24	258									

Caliper

	original	After 1st Run	Before Endurance	after Endurance
4531	95-100-105	100-107	105-109	—
30	91-102-103	98-102	105-106	
29	93-105-107	101-106	105-107	

Section I

4531
30
29

5 ni cupo plated very Thin with Cadmium 21/ Chg 15h 200 dis 100

4531	587	508	514	527	572	532	517	511	487	498	500	
30	510	506	525	518	509	538	517	503	490	500	501	
29	507	509	525	531	518	533	513	517	500	510	512	

Endurance

	63	65	66	118	119	170	171	222	223
4531	567	520	520	543	510	490	483	467	460
30	545	528	508	545	510	508	490	475	463
29	580	533	525	570	528	518	508	487	470

	274	275	326	327	478	479	580	581		632	
4531	457	443	432	433	371	355	321	323	Trouble with Nick		364
30	477	444	441	441	367	348	322	327			383
29	478	467	457	463	384	367	333	333			378

	3	663									
4531	257										
30	272										
29	267										

Caliper

	Original	After 1st. Run	Before Endurance	After Endurance
4536	89-102-102	97-104	103-104	—
35	88-100-104	96-102	103-102	
34	90-100-103	98-101	103-103	

Section I

4536 | 5 mi cups plated very thin
35 | with Copper. 21% Cby 15 h 200
34 | dup 100

4536	490	508	510	522	502	520	517	503	489
35	499	505	512	522	502	513	516	503	490
34	497	505	513	520	502	515	516	504	488

	516	495	560	500
	518	493	498	501
	517	490	499	500

Endurance

	65	67	68	120	121	122	123	224	225
4536	553	520	520	537	505	497	483	478	467
35	560	532	518	558	519	512	493	480	467
34	542	529	520	542	506	493	483	467	462

	276	277	328	329	480	481	582	583	684
4536	459	440	427	425	219	267	262	275	236
35	472	450	440	446	358	342	297	247	228
34	451	439	423	423	329	315	218	232	197

Finish Grind

	685
4536	229
35	233
34	193

Caliper

	Original	After 1st Run	Before Endurance	After Endurance
4596	90-99-99	94-98	104-105	
95	91-101-103	100-110	100-106	
94	87-97-100	94-98	96-100	

Section I

4596 5 Rzg Ni assembled with Fe packets
95 having no Mercury in the black mix
94 Chg 15 h 220 dis 100 21% Chg Fe 15 h 200 rate 6 before assembling with Ni

4596	488	493	471	490	490	489	497	493	480	
95	480	486	474	500	496	500	510	500	475	
94	497	473	476	493	492	497	500	497	475	

4596	488	473	466	479	
95	505	487	482	491	
94	505	467	478	486	

Endurance

	61	67	64	120	121	122	123	224	225	
4596	542	500	500	537	483	492	458	452	432	
95	558	530	532	553	504	492	477	471	454	
94	550	517	500	547	493	490	467	462	439	

	276	277	328	329	480	481	682	583		684
4596	432	406	380	392	300	300	165	167		167
95	455	432	407	397	283	267	167	178	Fresh Mix	220
94	467	418	397	379	309	298	207	200		195

685

4596	170									
95	216									
94	197									

Calipers

	original	after 1st Run	Before Endurance	after Endurance
4603	94-102-107	97-103	101-104	
02	86-99-101	93-100	98-100	
01	80-99-102	98-100	100-101	

Section I

4603 5 hr Chg'd 33% 150 Talw 100 rate 15 h
02 assembled black iron No Mercury which
01 been previously changed 15 h 200 rate
Then Recha 15 h 200 dis 100 21%

4603	553	490	497	488	465	446	458	455	467	450	453	455
02	658	575	561	550	585	533	540	537	533	535	540	545
01	651	580	565	543	547	529	528	530	525	530	532	533

Endurance

	65	67	68	119	120	171	172	223	224
4603	488	450	434	486	467	492	467	465	461
02	617	543	532	553	532	527	512	506	488
01	565	543	522	498	525	527	507	498	492

	275	276	327	328	479	480	581	582		633
4603	473	448	425	417	409	382	333	297	283	283
02	490	456	433	424	410	389	325	307	313	313
01	487	463	432	433	400	377	330	298	248	248

	644									
4603	263									
02	316									
01	256									

Calipers

	Original	After 1st Run	Before Endurance
4627	90-103-104	98-104	105-104
26	90-102-103	101-104	104-105
25	95-105-112	101-106	104-111

Section I

4627 5 Ni Reg Fe. run in 5% KOH. 15%
26 Carbonate Potash.
25 Chg 15 h 200 dis 100

4627	475	497	397	460	412	415	387	396	333	345	380	387	380	382
26	477	498	430	437	449	450	435	442	442	465	450	444	428	425
24	472	495	373	380	398	400	378	395	397	367	392	390	395	398

Endurance

	67	69	70	121	122	123	124	225	226
4627	328	352	323	237	233	220	237	176	177
26	417	433	408	300	325	342	313	228	233
24	357	380	352	267	263	297	288	217	212

	277	278	329	330	481	482	583	584		685
4627	113	123	91	91	45	43	62	60	Run-in 10% KOH 1/4	60
26	133	130	88	84	47	47	0	3		25
24	167	167	120	122	55	52	40	40		43

	686									
4627	69									
26	37									
24	43									

Calipers

	Original	after 1st Runs	Before Endurance
4633	93-104-105	101-105	109-108
32	89-101-103	99-105	107-108
31	91-101-102	100-105	104-105

Section I

4633	5 m. Reg Te run in 10% KOH. 10%
32	Carbonate Potash.
31	Chg 15 h 200 dw 100

4633	478	502	483	490	493	500	492	500	498	488	500	495	467	497
32	479	464	481	484	502	497	485	489	487	470	495	487	473	472
31	475	497	482	488	493	467	485	495	487	465	442	487	467	472

Endurance

	69	69	78	121	122	173	174	225	226
4633	545	509	500	500	500	520	500	500	483
32	533	516	493	508	487	497	477	478	467
31	532	515	493	518	498	520	487	497	480

	277	278	329	330	481	482	583	584	685	
4633	492	453	427	421	309	300	143	110	90	5% KOH 10% Sodium Carbonate
32	463	442	400	S.C.	190	174	67	63	49	
31	482	457	427	427	216	192	88	83	35	

	686
4633	110
32	67
31	50

Calipers

	original	after 1st Run	Before Endurance	After Endurance
4638	91-102-103	104-108	109-109	
36	92-101-107	101-107	110-109	
34	98-102-106	99-107	107-110	

Section I

4638
36
34

5 M KOH, 5% Carbonate
~~KOH~~ Potash – clg 15 h 200 dis 100

4638	505	507	500	519	513	521	517	510	515	518	513	520	502
36	457	493	488	506	490	507	513	500	522	493	497	500	490
34	478	503	497	512	507	515	517	511	523	519	512	515	505

Endurance

	66	68	69	120	121	122	173	224	225
4638	584	580	493	467	467	467	458	433	425
36	550	487	478	458	457	444	434	387	387
34	565	509	500	487	498	475	461	438	431

	276	277	328	329	460	481	582	583		634
4638	417	403	355	367	345	320	312	300	185 Pressed Pellet	253
36	377	366	292	293	267	253	192	185		105
34	420	407	341	367	346	325	283	272		260

	685									
4638	267									
36	175									
34	264									

Calipers

	Original	after 1st Run	Before Endurance
4664	90-99-103	105-101	107-105
61	91-101-102	102-103	101-103
60	91-98-101	100-101	104-104

Section F

4664 | 5 Ni Reg. mix dipped 3 minutes in our
61 | Sulphate Nickel Solution, dried on plate.
60 | Then put soak 120 hours in 33% down
stairs in bottle Then assemble + put in
21% Chg 15 h 200 dis 100

4664	442	493	524	518	521	525	526	507	512	515	
61	445	491	521	527	529	529	524	507	508	512	
60	440	498	523	527	515	522	522	510	516	517	
				Endurance							
	63	65	66	117	118	169	170	221	222		
4664	567	533	500	533	523	533	493	491	470		
61	560	542	526	510	530	541	508	500	482		
60	538	527	510	467	523	527	500	500	482		

	273	274	325	326	477	478	529	580		631
4664	467	438	406	393	329	284	210	200	Endurance 100	198
61	443	444	417	407	343	313	233	223		173
60	486	459	431	421	343	320	233	223		162

	632
4664	200
61	195
60	171

Calipers

	Original	after 1 1st Run	Before Endurance	
4668	92-100-104			
67	93-102-106			
66	89-100-101			
65	93-104-104			

Section I

4668	5 hr with 4lg in bottom saturated Zinc
67	1/16 Huck, chg 200 15 h dis 100 21½
66	
65	

4668	470	522	500	500	497	475	492	503	
67	471	513	495	492	490	467	473	495	
66	467	508	490	493	497	467	488	500	
65	478	518	471	493	473	488	465	503	

Endurance

	61	63	64	115	116	167	168	219	220
4668		452	460	367	442	408	434	405	432
67	493	452	445	368	433	377	401	313	310
66	505	483	515	407	467	415	438	373	388
65	498	498	463	400	450	400	428	395	409

	271	272	323	324	424	425	576	577	
4668	392	417	173	463	0	29	2	10	Pull in
67	442	205	561	0	0	0	6	3	pull in
66	297	233	171	108	76	65	32	47	pull in
65	372	280	233	233	67	65	17	16	RON.

	678	679	680	681	682	683				
4668	113	56	262	330	207	255				
67	93	117	130	263	213	258				
66	15	93	227	323	238	325				
65	38	103	197	310	208	263				

Calipers

	Big Calipers- original	after 1st Run	Before Endurance
4687	90-100-101		104-101
81	92-100-103		101-104
80	92-102-103		100-104

Section I

4682	5 m. Reg mix dipped 3 minutes in
81	Ammonia solution containing Chloride
80	Ammonia in which Ni hydroxide is dissolved - dried on plate soaked 156 hours in 33% down stairs 21% assembled rig Fe Chg 15h 200 dis. 106

	1	2	3	4	5	6	7	8	9	10		
4682	470	500	513	548	565	547	530	537				
81	487	508	519	532	533	548	532	546				
80	466	500	513	540	540	542	530	538				

Endurance

	63	65	66	117	118	169	170	221	222	
4682	598	547	532	542	530	540	512	500	488	
81	603	588	533	555	533	538	513	500	494	
80	593	547	533	553	537	543	520	510	497	

	273	274	325	326	477	478	529	530		681
4682	481	460	433	423	397	367	333	320	Taken off Mill	278
81	484	465	433	432	389	362	393	263		257
80	494	474	447	447	408	400	373	367		323

	682									
4682	267									
81	237									
80	337									

Calipers

	original	after 1st Run	before Endurance
4700	91-101-101	99-102	102-104
4699	90-102-100	98-103	101-105
98	92-101-102	101-105	104-106

Section I

4700	5 Rzg Ni 10 old runs Chg the 5 24 in
4699	33% as anode & 10 runs as Cathode
98	15 h 100 rate 150 Fahr both in same dish Then assemble in Cells 21% Chg 15 h 200 dis 100

4700	547	540	528	530	537	516	517	517	
4699	576	543	532	520	532	512	512	505	
98	565	527	527	523	530	508	513	485	

Endurance

	61	63	64	115	116	167	168	219	220
4700	567	508	492	508	477	520	471	467	442
4699	542	513	499	522	500	540	495	482	477
98	558	512	498	518	500	514	500	487	482

	271	272	323	324	475	476	527	528		579
4700	471	432	417	404	396	365	332	295	Tube 1st Run	266
4699	471	449	417	412	396	357	333	317	Tube 1st Run	262
98	479	454	419	417	397	357	345	318	Tube 1st Run	270

	630
4700	255
4699	248
98	233

Calipers

	original	after 1st Run	Before after Endurance
4724	99-99-102	95-100	101-104
23	92-102-103	100-104	102-106
22½	91-101-103	99-104	99-100

Section I

4724 5 mi Reconed 150 Tohn 5% ROH..
23 15 h 100 rate assemble with previous
22½ Chg 15 h 200 dr 100 21.%

	1	2	3	4	5			
4724	486	497	219	517	508			
23	483	497	212	509	499			
22½	484	495	217	515	505			

Endurance

	58	60	61	112	113	164	165	216	217
4724	548	520	511	533	478	529	497	495	481
23	533	523	511	508	513	537	503	492	486
22½	50	517	50	510	487	512	471	455	444

	268	269	320	321	472	473	524	525		576
4724	479	456	433	430	413	378	348	330	Endurance Test	298
23	480	457	433	433	400	373	350	348		297
22½	445	422	391	390	367	331	322	293		252

	627									
4724	290									
23	293									
22½	233									

Calipers

	Original	After 1st Run	Before Endurance	After Endurance
4734	87-101-100	95-101	100-103	
33	87-100-101	94-102	97-103	
32	90-102-102	99-103	100-103	

Section F

4734 5% Revised perforations chgd in
33 5% KOH. 150 Fahr 100 rate. 30 hours.
32 then assembled reg vents & chg 15 h 200 chs 100

	1	2	3	4	5	6
4734	622	538	518	511	530	513
33	618	58	540	512	528	511
32	619	538	523	513	530	515

Endurance

	59	61	62	113	114	165	166	217	218
4734	540	492	479	485	467	475	446	437	425
33	550	507	492	488	478	485	457	437	430
32	577	514	499	500	483	497	463	444	433

	269	270	321	322	423	424	575	576		627
4734	422	393	363	353	300	283	233	220	Taken off test	225
33	427	397	364	358	323	295	243	233		222
32	423	400	371	367	328	300	237	225		209

678'

4734	212								
33	212								
32	209								

Calipers

	original	1st Run	Endurance Before	Endurance After
4767	87-101-101	95-101	100-103	
66	90-100-103	97-103	102-105	
65	89-100-101	96-100	100-102	

Section I

4767 5 ni 21% made from stick KOff by
66 Alcohol chg 15h 200 dis 100
65

	1	2	3	4	5	6	7	8	9	10
4767	497	492	506	513	490	515	515	488	498	487
66	506	507	512	521	512	513	522	490	500	500
65	505	507	512	522	502	515	517	493	501	500

Endurance

	63	65	66	117	118	169	170	221	222
4767	540	517	507	522	507	518	496	489	477
66	587	533	511	533	523	537	507	499	488
65	577	524	511	508	527	528	500	492	480

	273	274	325	326	477	478	529	580		681
4767	476	477	473	416	383	375	492	253	Tensile strength	233
66	488	461	432	416	381	355	498	267		257
65	484	470	424	415	375	355	467	240		245

	682									
4767	230									
66	241									
65	214									

Calipers

	original	after 1st Run	Before after Endurance	Endurance
4777	91-107-104	101-103	103-104	
76	93-107-104	102-105	104-105	
75	93-105-103	101-105	105-106	

Section I

4777 5 ni Rwmed perf inside of cups
76 Cleaned with Emery paper —
75

	1	2	3	4	5
4777	499	507	517	510	515
76	496	506	513	510	512
75	501	507	517	512	515

Endurance

	58	60	61	112	113	164	165	216	217
4777	553	497	498	507	492	518	479	450	449
76	557	492	490	510	495	518	484	455	452
75	553	503	498	507	492	510	484	447	451

	268	269	320	321	472	483	534	535		586
4777	442	419	371	367	327	300	252	333	Mon Wt	233
76	446	425	378	378	331	312	267	350		230
75	441	418	363	361	312	283	233	339		239

	637
4777	215
76	213
75	220

Calipers

	Original	After 1st Run	Before Endurance	424th hr
4804	96-109-107	103-106	111-112	117-113
03	95-106-106	99-105	108-108	113-114
02	95-106-106	104-108	113-110	118-115

Section II

4804 5 hr 2½ which has been heated 130 Fah.
03 10 hours with ½ cts bulk of shavings
02 from a side guide rubber from E18 cell.
~~Keep~~ Keep KOH from Carbonating by moving a bottle + let it rest on Asbestos on hot plate downstairs need about 800 cc of 21%
Chg 15 hr 200 dis 100 —

4804	492	497	500	478	489	489	
03	500	504	510	492	497	496	
02	492	497	500	486	489	489	

Endurance

	59	60	111	112	163	164	215	216
4804	500	511	522	497	483	457	445	422
03	506	517	521	500	488	467	449	433
02	496	507	517	494	482	455	447	427

	267	268	319	320	371	372	423	424	525	526
4804	395	392	344	317	247	255	209	208	200	133
03	400	400	355	333	287	267	233	247	300	270
02	400	400	357	320	296	293	247	250	237	210

	627	628							
4804	95	153							
03	167	223							
02	158	195							

Calipers

	Original	After 1st Run	Before Endurance	424 hr run
4809	92-106-107	98-106	107-109	114-110
08	97-107-109	110-109	105-108	123-117
07	95-106-104	100-104	107-112	118-124

Section II

(800 cc 2½)

4809 | 08 | 07 — 5 M put in solution in which 10 Rubber pack rings, soft, from E 18 heat on hot plate down Jars the whole being in a Closed Bottle, glass Stopper, 15 hours. Use this Solution in Little Cells – Clip 15 h 200 dia 100.

4809	501	503	508	482	492	488	
08	492	497	500	477	481	482	
07	504	507	510	487	496	492	

Endurance

	59	60	111	112	163	164	215	216
4809	503	511	512	491	476	450	429	405
08	498	500	505	485	467	446	426	405
07	506	517	533	512	500	479	462	444

	267	268	319	320	371	372	423	424	475	476
4809	381	377	345	325	275	260	225	213	215	197
08	382	377	333	325	275	260	213	232	215	183
07	417	420	387	372	325	288	225	257	169	183

		627	628
4809	Run 1 to 424 hr	150	227
08		193	228
07		191	226

Calipers

	Original	after 1st Run	Before Endurance
4816	92-106-104	101-106	104-106
14	93-102-101	103-102	104-106
12	92-102-104	105-106	112-108

Section II

4816 5 ml. 1 gram precipt'd Magnesium hydroxide
14 in Zachariah 21/ Chg. 15h 200 cls 100
12

4816	512	507	543	533	526	512
14	510	500	535	523	512	503
12	493	493	503	525	512	505

Endurance.

	59	60	111	112	163	164	215	216
4816	498	507	508	487	482	457	425	394
14	506	517	539	514	517	492	482	462
12	500	508	512	491	477	452	433	412

	267	268	319	320	371	372	423	424	525	526
4816	367	365	367	346	310	295	215	233	160	187
14	438	446	405	388	330	312	252	265	213	200
12	387	390	333	306	257	247	216	232	158	167

		627	628							
4816	Broke Jump Rope	163	223							
14		281	287							
12		182	222							

Calipers

	Big Caliper Original	after 1st Run	Before Endurance
4840	102-111-115	113-113	112-114
39	100-111-113	105-107	115-113
38	97-108-110	112-114	118-116

§ Section II

4840 5 Ni to 62 charged 15 h 200 rate
39 given to Edison after chg. He will put them in large quantity water until Every Trace
38 Potash comes out. Then they are to 62 put back on 21% + charged again 15 hours 200 rate + dis 100

4840	528	555	563	570	478	566	554	
39	530	555	563	573	559	567	565	
38	525	556	563	567	553	562	552	

Endurance

	60	61	112	113	164	165	216	217
4840	561	570	568	558	556	522	507	477
39	560	567	571	550	550	521	499	473
38	558	563	565	542	550	497	462	439

	268	269	320	321	372	373	424	425	526	527
4840	442	446	383	371	333	315	268	250	230	250
39	442	447	385	386	363	358	333	312	212	220
38	414	400	319	300	200	289	259	245	145	160

CO

	628	629
4840	250	283
39	247	256
38	160	225

Calipers

	Original	After 1st Run	Before Endurance
4850	94-107-107	105-109	106-109
49	95-107-108	104-109	107-107
48	93-107-107	104-108	106-108

Section II

4850 | 5 Ni reversed perfo sent to Phenolics
49 | plated heavier. Chg 15 h 200 cls 100
48 |

4850	505	512	533	532	518	517	532	
49	511	512	533	533	517	507	530	
48	505	512	452	533	535	523	533	

Endurance

	60	61	112	113	164	165	216	217
4850	514	519	533	511	494	475	457	445
49	512	519	532	507	486	476	467	452
48	513	517	533	510	500	475	466	447

	268	269	320	321	372	373	424	425	526	527
4850	416	421	367	365	357	352	345	330	312	310
49	414	428	380	375	363	361	353	330	330	320
48	424	427	380	383	370	367	367	370	367	367

	Pre Endurance Run	628	629
4850		191	208
49		192	212
48		267	283

Calipers

	Original	After 1st Run	Before Endurance
4855½	91-105-104	100-105	104-106
55	94-109-105	98-103	110-109
54	93-104-104	97-103	103-105

Section II

4855½ 5 Mx Rewound Perfo run on 21% Sol 800 cc in
55 Bottle put on hot plate 24 hours
54 Containing 1/3 cts bulk of separators from Glen Ridge which are ready to go into Cells or taken from an old E18 cell have break up in 1/8 x 1/16 long pieces (Moulded) then fill little Cells from this Solution

4855½	493	497	503	497	510	500	
55	492	497	503	492	511	500	
54	493	498	508	500	513	517	

Endurance

	59	60	111	112	163	164	215	216
4855½	527	525	522	506	494	474	457	439
55	509	507	522	498	486	461	446	426
54	522	520	543	517	509	475	467	440

	267	268	319	320	371	372	423	424	527	526
4855½	419	427	355	354	359	348	312	275	333	200
55	403	407	339	333	328	311	292	263	300	233
54	416	419	362	346	360	348	320	292	313	275

		627	628							
4855½	5½	190	220							
55	5½	205	230							
54	5½	210	242							

Calipers

	Original	After 1st Run	Before Endurance
4858	97-106-105	102-108	105-107
58	93-103-106	100-105	106-108
57	92-105-106	101-105	105-107

Section II

4859	Dup of 4855½ Except the 800 cc of
58	21% has 1/3 its bulk of new separators
57	Cut from sheet

4859	500	495	503	517	517	513	
58	498	495	503	531	517	507	
57	498	498	507	483	518	510	

Endurance

	59	60	111	112	163	164	215	216
4859	505	512	518	498	496	472	457	442
58	498	504	500	481	476	447	434	400
57	500	510	512	493	486	461	439	418

	267	268	319	320	371	372	423	424	525	526
4859	413	418	367	343	310	300	262	250	225	227
58	377	377	300	285	277	264	230	227	225	228
57	398	400	333	325	294	291	250	240	193	202

	627	628								
4859	200	242								
58	162	197								
57	169	215								

Calipers

	original	after Run	before Endurance
4864	97-104-105	105-106	109-108
63	98-105-105	98-103	105-104
62	98-108-109	105-109	106-108

Section H

4864	5 M Removed perf dup 4855 Except,
63	800 cc 21% heat 1/3 bulk of fine shavings
62	from the thin sheet rubber on sides of 2.18 –
	Chg 15 h: 200 dis 100

4864	492	500	513	580	532	528		
63	493	485	498	539	515	512		
62	500	493	503	533	517	514		

Endurance

	59	60	111	112	163	164	215	216
4864	520	532	550	525	537	504	507	485
63	505	512	524	497	488	459	444	418
62	500	508	513	492	487	459	446	419

	267	268	319	320	371	372	423	424	525	526
4864	459	466	423	421	423	412	387	345	360	345
63	394	393	333	329	322	292	262	250	248	242
62	392	392	319	319	300	267	265	257	227	260

	627	628								
4864	252	258								
63	178	230								
62	160	210								

Calipers

	Original	after 1st Run	Before Endurance
4878	93-104-106	104-104	106-108
77	95-106-108	104-105	108-106
76	93-107-106	103-107	107-107

Section II



4878	5 pts made up 3 sections, uncrevurved parts
77	use 1070 milgrmt in each section.
76	21% chg 15 h 200 cl.s 100

4878	500	503	505	504	512	488	526	500	507	495
77	508	518	517	515	522	498	538	509	523	505
76	508	518	520	517	523	498	536	507	523	500

Endurance

	59	60	115	116	167	168	219	220
4878	489	497	496	477	467	441	422	400
77	497	505	504	492	477	461	443	429
76	497	505	507	487	467	445	428	409

	271	272	323	324	375	376	427	428	529	530
4878	287	277	319	320	300	292	263	247	198	185
77	407	411	353	357	347	333	303	267	258	228
76	291	296	337	330	310	300	277	258	235	229

	631	632
4878	133	157
77	183	219
76	143	177

Tensile Strength

Calipers

	Original	after 1st Run	Before Endurance
4885	93-101-103	101-106	107-105
84	90-102-102	100-103	105-106
82	93-101-105	100-104	106-102

Section II

4885 .5 M Renewed Pafs - 2 grms gelatin
84 dio in 21% KOH in each cell.
82 Chg 15 h. 200 dio 100

4885	433	498	502	300	367	453	510	
84	433	490	425	300	400	459	500	
82	417	490	460	425	433	467	500	

Endurance

	60	61	112	113	164	165	216	217
4885	517	506	400	400	550	539	512	509
84	511	506	333	433	544	531	507	494
82	527	524	341	400	553	531	505	486

	268	269	320	321	372	373	424	425	526	527
4885	482	487	387	380	253	247	143	132	112	97
84	471	474	383	367	233	223	143	133	80	83
82	461	467	342	333	228	207	117	122	110	122

Note Curve is very broad. Drops to low voltage like expanded time. - D.E.H.

	Breaking Strength									
4885	72	108								
84	113	162								
82	117	145								

Calipers

	Original	after 1st Run	Before Endurance
4900	95-104-103	93-102	106-103
4898	89-98-99	99-106	101-99
96	83-96-99	97-94	95-97

Section II

4900 5 hr Reg put in old C Cups 1250 hole
4898 21% chg 15 hr 200 dia 100 — not new pay
4896

4900	478	473	483	480
4898	477	485	488	482
96	470	473	490	478

Endurance

	57	58	109	110	161	162	213	214
4900	467	482	492	477	470	447	443	430
4898	478	493	495	485	480	462	456	442
96	472	483	492	467	461	439	432	411

	265	266	317	318	369	370	421	422	525	526
4900	409	411	361	372	392	387	387	355	332	333
4898	420	423	377	379	397	390	358	323	343	297
96	395	397	342	333	353	340	312	265	187	198

	Before Endurance Run		625	626
4900			256	250
4898			243	277
96			194	223

Calipers

	Original	After 1st Run	Before Endurance
4903	97-106-107	105-107	109-108
02	96-106-107	105-107	109-106
01	94-102-105	107-107	110-106

Section II

4903 — Reversed perf old C cups
02 — 21% chg 15 h 200 cls 100
01

4903	478	488	492	485
02	477	488	492	484
01	483	487	487	483

Endurance

	57	58	109	110	161	162	213	214
4903	480	492	511	487	483	452	428	415
02	487	492	500	480	462	433	400	390
01	472	482	492	465	450	424	396	386

	265	266	317	318	369	370	421	422	523	524
4903	397	392	328	333	333	333	320	265	150	162
02	377	367	278	394	267	267	278	222	155	163
01	377	367	247	394	267	267	263	212	145	147

	625	626
4903	162	176
02	167	175
01	127	153

Bond strength Rod Yield

Calipers

	original	After 1st Run	Before Endurance	422 mod mm
4909	88-100-98	99-99	102-99	118-117
08	91-101-103	99-104	102-105	116-113
07	93-104-104	100-104	105-104	118-115

Section II

4909 .5 ml put in 5000 hole Cups -
08 chg 15 h 200 dwl ing -
07

4909	485	497	492	488	
08	487	500	497	492	
07	490	500	497	491	

Endurance

	57	58	109	110	161	162	213	214
4909	487	496	504	487	488	457	443	467
08	504	509	523	505	512	477	453	460
07	497	505	511	499	500	470	450	476

	265	266	317	318	369	370	421	422	473	474
4909	425	423	367	383	393	372	190	333	160	155
08	447	442	392	390	397	397	367	353	329	328
07	433	433	377	394	390	383	367	357	167	179

	0	425	426							
09	Before Endurance	153	157							
08		250	203							
07		185	192							

Calipers

	Original	After 12 Hr. Run	Before Endurance
4060C	98-100-101	96-102	105-105
B	98-99-101	97-102	102-102
A	89-100-102	99-104	106-109

Section I

4060C Reg pockets 3.2 gms
60B Reduced perforations
60A Smooth press 10.0 comp 7.5
Charged new set 15 hrs in 33% KOH
assembled with charged covers
Chg 15 hrs @ 200 disch @ 10.0

	1	2	3	4	5	6		
4060C	539	534	543	458	367	532		
B	533	529	536	450	383	522		
A	522	515	532	367	375	508		

Endurance

	59	61	62	113	114	165	166	217	218
4060C	592	543	507	543	522	495	483	458	442
B	542	522	483	512	488	460	450	442	417
A	547	508	467	508	467	438	420	380	400

KOH spilled just in here

	269	270	321	322	473	424	525	526		477
4060C	428	393	352	351	285	260	230	250	Fresh KOH 33%	241
B	400	375	340	332	257	257	265	263		229
A	367	338	310	297	249	207	50	wire broke		212

	478								
4060C	233								
B	222								
A	183								

Caliber

	Original Run	Before Endurance
4060F	87-100-99	102-108
E	94-102-102	98-106
D	92-100-104	92-110

Section I

4060F Reg pockets 3:2 guns
E Revised perforations.
D Smooth press 100 comp 75
charged reg. 15 hrs in 33% KOH
assembled with charged wires
Chg 15 hrs @ 200 discha @ 100

4060 F	517	535	529	358	375	522			
E	523	535	525	412	383	S.C.	521		
D	521	518	530	358	333	527			

Endurance

				113	114	165	166 217		218
4060 F	538	508	483	500	478	483	447	415	403
E	543	510	483	508	492	460	457	433	417
D	572	508	492	508	461	447	433	400	402

Chilled KOH put in new

	269	270	321	322	473	474	575	576			477
4060 F	390	354	337	330	S.C.	180	S.C.	217			193
E	400	389	347	342	200	260	228	227			216
D	367	333	317	288	250	235	250	264			184

	479
4060 F	213
E	206
D	185

Calipers

	Original	after 1st Run	Before Endurance
4061C	87-97-103	110-116	105-108
B	89-102-103	102-108	99-105
A	86-98-102	100-102	102-99

Section I

4061.C Reg expo #38.5. No mix 3.2 gms
B Fine graphite sprinkled on inside
A of expo. Pressed reg mix
with reg mix
chg 200 discha 100

500

	1	2	3	4	5	6
4061.C	518	533	529	479	491	522
B	540	545	541	496	508	533
A	535	543	533	471	483	524

Endurance

	59	61	62	113	114	165	166	217	218
4061C	585	547	532	544	515	527	503	493	482
B	583	552	550	555	528	523	512	508	495
A	573	547	533	533	523	517	507	497	496

	269	270	321	322	373	424	525	526		477
4061C	481	465	442	457	398	395	367	390		293
B	489	477	452	460	350	345	175	178	Break Thru Flow	197
A	489	465	443	467	417	393	378	383		350

	478
4061C	336
B	195
A	349

Calipers

	Original	after 1st Run	Before Endurance
4112	88-98-107	98-108	100-100
11	85-98-99	96-102	95-100
10	88-100-100	100-104	103-103

	684	685
4112	149	157
11	52	90
10	79	93

Section I

4112 Reversed perforations 3.2 Rey
11 mix to be changed .15 lbs 200 ~
10 dischy 100 2.1 %

	1	2	3	4	5	6	7	8	9	10
4112	525	524	528	528	517	537	533	520	517	512
11	530	532	534	528	532	550	550	533	527	525
10	533	529	527	523	518	547	543	532	525	519

	11	12	13
4112	515	357	507
11	527	371	513
10	525	384	520

Endurance

	66	68	69	120	121	122	123	224	225
4112	510	500	497	492	467	433	440	400	400
11	512	504	502	524	481	438	447	433	413
10	500	483	486	467	447	417	420	387	382

	276	277	328	329	480	481	582	583	
4112	367	337	330	320	214	212	160	167	Breaking Strength
11	400	378	353	352	189	198	165	162	
10	352	317	302	287	159	150	100	108	

Calipers

	Original	After 1st Run	Before Endurance
41 99	87-100-101	101-102	99-100
98	94-101-101	100-102	104-105
97	90-100-103	95-100	100-101

697 685

4199	97	97								
98	145	143								
97	148	169								

Section F

4199 | 4 mi rerun = 15 hrs 100 rate
98 | @ 150° F in 33% otale KOH +
97 | against C.P. Ni strip
charged and discharged in 2.1% 150 H
chged 15 hrs @ 200 rerun @ 100.

	1	2	3	4	5	6	7	8	9
4199	476	500	457	489	500	509	511	496	522
98	478	490	467	492	500	509	512	487	520
97	487	493	466	487	510	514	517	490	527

	10	11	12	13	14	15	16		
4199	498	509	507	510	506	580	503		
98	498	509	503	510	516	532	500		
97	500	517	508	514	516	537	515		

Endurance

	69	71	72	123	124	175	176	227	228
4199	567	533	524	532	500	493	472	467	453
98	570	523	532	538	511	507	500	493	473
97	567	533	533	557	529	520	515	507	492

279 280 331 332 483 484 585 586

4199	447	417	408	395	133	140	27	43	
98	467	458	437	442	300	293	77	87	
97	481	468	453	457	367	363	229	233	

Ni Cyanide

Calipers

	original	after 1st Run	Before Endurance
42-13	88-100-101	99-100	98-103
11	88-98-102	96-104	97-104
09	89-99-101	100+102	110-105

Section F

42-13 | 5 hr. charged 15 hrs @ 200
11 | @ 175°F in Tumbler containing
09 | 33⅓% KOH and 4 grms. silicate Soda
Charged & discharged in 2 hr
Chg 15 hrs @ 200 run @ 100.

	1	2	3	4	5	6	7	8	9
42-13	638	S.C.	567	497	503	508	510	503	495
11	607	552	517	482	484	453	467	413	416
09	703	733	708	673	659	642	647	600	597

Endurance

	62	64	65	116	117	168	169	220	221
42-13	490	525	523	527	510	508	507	487	473
11	433	442	455	450	447	438	447	417	408
09	531	528	537	526	512	493	500	467	467

	272	273	324	325	476	477	528	529	
42-13	475	450	425	467	350	337	447	S.C.	Finished 1950
11	400	377	350	342	238	233	328	227	
09	443	425	415	413	300	227	220	217	

	680	681								
42-13	233	230								
11	226	228								
09	200	210								

Calipers

	original	after 1st Run	Before Endurance
4266	88-103-101	98-102	100-101
65	91-104-104	100-108	101-105
64	89-102-97	97-100	98-99

	273	274	325	326	477	478	579	580	Endurance Run	691
4266	467	427	426	418	267	255	182	182	4	1108
65	487	442	409	413	250	220	255	265	Hours	719
64	449	417	402	397	262	238	167	167		140

	652											
4266	110											
65	230											
64	152											

4266												
65												
64												

Section F

4266 | 5 hrs + 4 hrs Mix, Mix dried 2 hrs
65 @ about 220° before putting in
64 | pockets and quickly used.
Soaked 96 hrs in 33⅓% KOH, in
big bottle on hot plate Amp Temp 144°F
Pockets heated 4 hrs @ 220°F and
plunged quickly in 33⅓%
Time elapsed from taking out of
bottle and assembling with irons
that have been run was 30 sec
Charge 15 hrs @ 200 discharge @ 100 in 21%

	1	2	3	4	5	6	7	8	9
4266	385	442	473	492	447	491	490	484	483
65	417	488	487	508	468	521	517	502	511
64	385	460	473	485	446	500	490	489	477

	10											
4266	487											
65	515											
64	490											

Endurance

	63	65	66	117	118	169	170	221	222
4266	547	526	522	532	505	530	500	493	470
65	590	562	548	583	517	532	577	497	470
64	547	530	523	530	505	488	482	473	455

Calipers

	Original	after 1st Run	Before Endurance
4356	92-102-103	100-104	104-104
55	90-101-104	97-102	102-103
54	91-102-104	99-105	103-105

	621	622
4356	398	266
55	267	254
54	302	293

Section I

4356 | 5 hrs charged @ 150° F 15 hrs
55 | @ 100° against C.P. hi strip
54 | in 33% KOH in tumbler glass used instead of rubber
Soaked 6 hrs in 21%
Charged 15 hrs @ 200 discha @ 100 in 21%

	1	2	3	4	5	6	7	8	9
4356	650	532	554	547	545	506	532	533	518
55	643	532	547	542	547	508	532	525	513
54	633	532	548	546	543	507	532	525	513

	10
4356	517
55	517
54	512

Endurance

	63	65	66	117	118	169	170	221	222
4356	590	562	547	540	518	512	500	493	477
55	593	562	547	557	507	532	507	492	490
54	607	562	549	566	533	500	515	497	492

	273	274	325	326	477	479	529	580	
4356	467	454	447	443	357	345	267	260	Tumbled 15 hrs @ 100 in 21% KOH
55	477	455	433	467	363	360	297	295	
54	491	470	447	467	397	393	228	250	

Calipers

	Original	after 1st Run	Before Endurance
4361	89-109-110	105-108	104-106
60	88-109-110	105-107	108-110
59	89-110-111	100 + 102	104-107

	659	660
4361	218	223
60	209	216
59	197	204

Section I

4361 | 5 Reg. Ni pressed @ 50 tons.
60 | heat in hot plate + lower.
59 | slowly in 33% Drake 6 hrs.
assembled into cells in 33% KOH.
Charged 15 hrs @ 100. @ 150° F.
disconnected nickels and soaked
10 hrs in large jar of water
then dried on hot plate 3 hrs.
at 125° F
Smooth press 100. Corrugated 75.
Assembled in cells and charged
again 15 hrs @ 100 discha 100.

	1	2	3	4	5	6	7	8	
4361	570	567	570	515	533	S.C.	507	530	
60	583	582	575	537	539	523	520	530	
59	518	518	525	513	516	495	490	508	

Endurance

	61	63	64	115	116	167	168	219	220
4361	547	531	532	523	485	492	483	467	467
60	553	546	532	537	518	505	500	488	475
59	588	545	522	533	500	492	477	467	467

	271	272	323	324	475	476	527	528	
4361	450	429	422	412	348	332	267	253	5.1
60	458	443	430	423	352	347	258	248	5.1
59	456	422	408	398	307	279	220	215	5.1

Calipers

	Original	After 1st Run	Before Endurance
4387	86-99-99	94-99	98-101
86	89-101-103	96-104	99-104
85	90-102-103	100-104	105-108

	275	276	327	328	479	480	581	582		683
4387	487	463	456	442	383	167	40	43	Start Endurance	142
86	500	486	477	477	400	390	387	357		254
85	438	417	415	398	283	227	255	215		158

	684											
4387	164											
86	255											
85	165											

4387												
86												
85												

Section I

4387 | 5 hrs. Charged 15 hrs @ 100
86 | against C.P. Ni strip @ 150°F
85 | in 33% and then assembled with irons charged 24 hrs @ 200 in 21% KOH @ 150°F. The cell after assembling is to be discharged @ 100. with out further charging.

	1	2	3	4	5	6	7	8	9
4387	413	535	525	263	497	521	520	517	515
86	418	553	547	217	491	520	8.C.	8.C.	498
85	443	605	567	545	540	548	535	554	538

	10	11	12							
4387	519	521	513							
86	510	509	510							
85	554	558	547							

Endurance

	65	67	68	119	120	171	172	223	224
4387	552	533	522	543	518	532	507	505	490
86	538	533	522	543	524	532	508	523	500
85	562	543	522	532	512	492	485	467	467

Calipers

	Original	After 1st Run	Before Endurance
4391	93-103-104	100-105	93-102
90	91-102-104	99-106	104-106
89	92-103-104	100-106	100-104

	630	641
4391	183	193
90	242	251
89	257	260

Section I

4391 | 5 min. charged 1.5 hrs @ 100
90 | min 22% @ 150° F. Soaked
89 | 10 hrs in 21% then charged
15 hrs more @ 200 against C.S.
Ni strip then assembled with
irons which have been charged
24 hrs @ 200 in 21% @ 150° F.
After assembling discharge @ 100

	1	2	3	4	5	6	7	8	9
4391	552	554	525	525	457	532	532	527	527
90	588	555	528	528	455	389	527	537	537
89	580	58[illegible]	483	479	423	345	8[illegible]	8[illegible]	

Endurance

	62	64	65	116	117	168	169	220	221
4391	594	553	547	555	525	505	508	492	493
90	606	553	547	550	525	510	507	490	480
89	563	546	522	544	513	523	506	500	482

	272	273	324	325	476	477	628	629	
4391	478	458	433	8[illegible]	342	320	333	293	Fully charged
90	467	453	440	467	383	368	313	313	
89	487	454	444	437	367	360	300	300	

Calipers

	original	after 1st Run	Before Endurance
4396	90 - 100 - 103	97 - 103	102 - 105
95	92 - 101 - 105	98 - 103	104 - 105
94	92 - 102 - 104	100 - 105	104 - 106

Section I

4396	Same as 4389 but with
95	reverse perforations
94	

	1	2	3	4	5	6	7			
4396	547	530	549	547	530	522				
95	543	530	552	547	522	530				
94	543	532	551	530	517	528				

Endurance

	60	62	63	114	115	166	167	218	219
4396	570	527	515	522	538	455	450	412	410
95	575	543	522	522	498	458	450	427	412
94	570	543	520	525	498	483	467	452	438

	270	271	322	323	474	475	526	527	
4396	388	361	333	333	232	265	217	200	5:1
95	400	372	347	338	229	217	200	193	4:1
94	428	375	369	353	215	200	167	167	3:1

	628	629							
4396	136	155							
95	130	159							
94	122	111							

Calipers

	Original	after 1st Run	Before Endurance
4406	96-107-107	105-110	119-111
05	96-106-109	105-110	125-116
04	100-110-111	110-114	121-117

	271	272	323	324	475	476	577	578	Avg. Thickness	679
4406	391	379	327	295	207	200	158	175		.100
05	347	337	318	297	215	209	216	220		.109
04	367	354	312	291	196	198	80	150		.116

	680
4406	117
05	197
04	139

Section I

4406 | 5 hr made dry mix Made
05 | from 8mm nickel and powdered
04 | in agate mortar very fine
rolled without water 8 + 2 of the
graphite. One part screened & one
part coarse 3.2 gram. cakes
Pierced perforations
Charged 15 hrs @ .100 against nickel
strip in 33% @ 150° F then washed
10 hrs in 21.9% KOH
Charged again 15 hrs @ 200 against
nickel strip and assembled
with irons charged 24 hrs @ 200
in 21% @ 150° F and discharged @ 100

	1	2	3	4	5	6	7	8	
4406	612	605	567	545	552	555	540	500	
05	642	612	567	553	567	571	555	567	
04	622	593	558	535	548	554	527	558	

Endurance

	61	63	64	115	116	167	168	219	220
4406	540	515	518	483	472	455	451	433	433
05	540	530	550	440	453	443	452	383	400
04	537	512	522	467	467	438	433	400	400

Calipers

	Original	After 1st Run	Before Endurance
44.16	92-102-102	96-104	102-105
15	95-98-99	95-100	98-102
14	89-99-105	98-104	103-103

	679	680								
4416	110	116								
15	127	124								
14	120	127								

Section I

4416 5 hrs reverse perforations
15 soaked 24 hrs in 33% @ 150°F
14 Soaked 12 hrs in large jar water
Dried on hot plate on paper
Then reconditioned @ 75 atmos
Charged 15 hrs @ 100 against CP nickel strip in 33% KOH @ 150°F
Soaked 10 hrs in 21% and assembled in cells with rinse charged 24 hrs @ 200 hot after assembling
Chg 15 hrs @ 200 at rack @ 100 in 21%

	1	2	3	4	5	6	7	8	
4416	598	519	532	457	533	541	533	531	
15	587	513	528	452	532	532	522	525	
14	597	520	527	543	537	542	532	533	

Endurance

	61	63	64	115	116	167	168	219	220
4416	557	545	521	525	491	467	467	432	418
15	570	516	508	508	473	452	450	400	408
14	574	534	521	522	485	458	447	397	387

	271	272	323	324	475	476	527	528	
4416	408	392	352	345	200	191	93	117	4.14
15	390	382	333	343	222	207	117	143	4.05
14	391	367	340	322	214	200	133	150	4.05

Calipers

	Original.	after 1st Run	Before Endurance
4589	122-120-117	146-135	154-135
88	122-118-118	145-136	153-134
87	121-120-116	147-134	155-129

	650	651
4589	347	370
88	330	350
87	345	353

Section I

4589 | 3.7 ni 3.84 gm # 21.8% fwts
88 | 2.56 ni(@ 14)
87 | Poured 100 smooth 100 corrugated with Goddards concave & convex dies. Material loaded in outside cup. The inside cup being concave. Put in 21% KOH & chg regular with two reg charged. Fee.
Run 5 times @ 100 # 5 times @ 500

	500 watts									
4589	570	581	579	525	533	500	575	563	582	
88	569	578	577	533	525	600	570	558	580	
87	570	573	575	533	550	50	567	558	565	

Endurance

	62	64	65	116	117	168	169	220	221	
4589	650	577	600	653	647	604	587	583	575	
88	648	600	590	643	609	610	593	577	575	
87	617	600	580	640	607	597	583	578	562	

	272	273	324	325	476	477	528	529		
4589	597	576	580	600	497	485	360	355		Run 5 times @ 500 watts
88	583	572	567	602	508	512	412	402		
87	579	567	573	600	514	516	413	493		

Calipers

	Original	after 1st Run	Before Endurance
4592	101-97-97	109-104	117-107
91	102-98-98	114-110	118-99
90	102-96-99	114-109	117-103

	680	681
4592	100	127
91	217	317
90	206	220

Section I

4592 | 3 mi 3.12 gms # 424 Reg. Hi Mix
91 | Reverse perforations of reg. strip
90 | Hi plating (cups marked H(+K0H)
Goddards concave - convex dies
Inside cup beaded in regular way
Pressed 100 smooth 100 corrugated
Run in 2190 against 2 charged Fers.
Run 3 times @ 100 + 3 times @ 500

500 watt

4592	515	526	525	417	442	400	537	517	527
91	512	527	528	417	425	425	548	517	530
90	508	522	522	417	421	392	533	528	519

Endurance

	62	64	65	116	117	168	169	220	221
4592	596	533	530	557	517	492	477	458	45
91	558	543	542	573	532	498	490	458	461
90	567	531	520	547	509	493	480	458	457

	272	273	324	325	476	477	578	579	
4592	450	418	362	367	266	240	130	140	5 min.
91	449	421	363	377	300	292	257	255	1 hour
90	444	415	363	372	264	268	98	88	2 hours

Calipers

	Original	After 1st Run	Before Endurance
4914	93-103-103	105-109	110-106
12	94-103-104	105-105	111-107
11	89-101-107	92-107	109-106

Section II

4914 5 hr in 5000 hole emps
12 Reamed perforations. 3.12 7.19.70
11 chg 15 hrs @ 200 Rum @ 100

4914	487	500	482	494								
12	480	492	489	477								
11	478	488	487	481								

Endurance

	57	58	109	110	161	162	213	214	265	266
4914	500	515	533	500	509	470	467	490	452	447
12	480	495	513	478	487	451	443	460	421	421
11	480	493	507	477	484	447	437	457	412	414

	317	318	369	370	421	422	533	534		625
4914	392	393	414	412	411	397	353	367	Bore Hole Emps	293
12	348	360	367	367	362	338	348	347		230
11	327	343	350	365	344	325	329	327	Perforations	250

	626
4914	286
12	225
11	243

Calipers

	Original	After 1st Run	Before Endurance
4921	98-98-102	96-100	
20	88-100-103	97-104	100-104
19	88-100-100	96-102	100-103

Section #5

1921 Group of 10 hrs old iron mill
20 do Made anode in 3370
19 @ 100 rate for 15 hrs assembled with reg nickels
Changed 15 hrs @ 200 discharg @ 100

4921	508	517	505	508	513	520	502	499	500		
20	505	503	447	500	500	514	495	493	495		
19	500	510	502	487	503	513	490	499	500		

Endurance

	62	63	114	115	166	167	218	219	270	271
4921	514	525	547	515	522	483	475	497	457	456
20	488	508	533	500	489	447	433	455	407	394
19	506	523	543	513	514	477	474	497	456	452

	322	323	374	374	426	427	529	529		630
4921	392	400	406	400	377	333	268	220	Reg Nickel	320
20	300	325	283	300	294	255	167	179	Reg Nickel	219
19	380	393	397	393	367	330	273	243	Reg Nickel	253

631

1921	277										
20	228										
19	243										

Calipers

	Original	After 1st Run	Before Endurance
4927	90-101-102	98-102	109-105
26	91-102-103	97-103	105-106
25	90-99-101	97-103	108-104

633

4927	217						
26	240						
25	248						

Section II

11927 5 nichols Reversed perforations
26 21 70 1 C.O.H. put in little cell 2 gram
25 Sulphate of Potash
Chged 15 hrs @ 200

4927	488	514	508	505	497	525	512	507	508	500
26	486	573	505	497	497	525	512	508	508	500
25	486	510	503	505	495	523	517	508	570	500

4927	498									
26	498									
25	500									

Endurance

	64	65	116	117	168	169	220	221	272	273
4927	505	518	531	500	500	446	445	467	423	419
26	500	516	522	503	498	461	433	403	427	422
25	506	520	517	500	487	457	429	455	398	394

	324	325	376	377	428	429	530	631		632
4927	348	352	343	333	293	232	165	167	Ends Split 1000	147
26	347	353	342	333	295	260	187	190	Ends Split 1000	219
25	315	327	313	300	294	260	190	193	Ends Split 1000	224

Calipers

	Original	after 1st Run	Before Endurance
4938	101-101-105	102-106	108-106
36	89-103-103	98-103	102-105
34	90-101-102	99-102	103-105

Section II

4938 | 5 Nichols Rivaled perforations
36 | 21 o/o ICO lbs. containing 5 grammes
34 | of Cyanate of potash (not cyanide).
Aug 15 hrs @ 200 · Run @ 100

4938	463	480	495	467	463	495	
36	458	478	475	467	433	467	
34	465	490	493	473	464	495	

Endurance

	59	60	111	112	163	164	215	216	267	268
4938	499	507	529	513	508	464	462	495	439	437
36	493	500	505	477	487	445	433	467	425	421
34	498	507	530	514	507	458	453	495	444	440

	319	320	371	372	423	424	525	526		629
4938	357	367	365	365	342	332	177	187	Total Cyanide used	280
36	353	350	348	333	367	358	167	183		227
34	373	391	380	367	300	297	138	178		255

	628
4938	252
36	227
34	180

Calipers

	Original	After 1st Run	Before Endurance
4948	92-102-104	99-103	99-105
47	94-103-105	99-104	103-105
46	93-102-105	100-107	105-106

Section II

4948 | 5 Nichols in 21% Revised
47 | perforations containing 3
46 | grammes of sugar
Chgd 15 hrs @ 200 discharged @ 100

4948	455	491	500	502	483	497						
47	455	498	507	502	467	465						
46	38	487	527	502	486	497						

	59	60	111	112	163	164	215	216	267	268
4948	525	521	528	525	497	464	447	467	476	424
47	467	481	488	463	472	441	430	453	407	397
46	520	528	523	477	497	445	442	460	416	414

	319	320	371	372	423	424	525	526	627
4948	272	56	313	56	298	273	177	177	188
47	293	092	292	250	180	167	97	108	150
46	333	357	343	333	252	224	177	167	218

Pressure 2 hrs 100 kg/cm²

	628
4948	212
47	160
46	197

Calipers

	Original	after 1st Run	Before Endurance	after 272 Runs
4958	114-109-109		107-100	125-110
57	114-110-110	109-103	107-100	127-116
54	112-107-110		100-107	125-112

Section II

4958 | 5 Nickel Riveted perforations
57 | Cups made with new 5.5 inch
54 | corrugations. No smooth die used
but only one pressure used & that
with new die,
Press 5 atmos 2 1/2 dwell 1.5 sec drawdy @ 100

4958	400	390	367	367	367	367	344	353	347	347
57	336	293	271	277	269	279	250	240	249	247
54	357	323	308	314	300	310	291	290	295	290

Endurance

	63	64	115	116	167	168	219	220	271	272
4958	233	300	267	258	230	195	156	134	167	165
57	190	185	167	155	133	133	88	100	100	97
54	238	267	219	197	167	143	117	133	125	121

4958											
57											
54											

CO Dept of Regrets to 200 atmos

4958											
57											
54											

Calipers

	Original	after 1st Runs	Before Endurance	after 272 Runs
4963	112-108-112	117-111		128-110
61	114-110-111			127-118
60	115-110-114			130-120

Section II

4963 Dup. of 4954 with 1.0 atmos
61
60

4963	433	420	416	407	412	405	488	392	397	380
61	443	429	417	433	432	424	408	430	419	400
60	449	432	417	420	425	417	400	398	400	392

Endurance

	63	64	115	116	167	168	219	220	271	272
4963	38	333	345	328	290	267	222	233	185	183
61	382	394	350	333	290	267	222	238	195	195
60	382	394	347	388	298	297	238	256	200	195

4963
61
60

CO

4963
61
60

Calipers

	Original	after 1st Run	Before Endurance	after 272 Run
4968	113-108-110	118-113		120-116
67	114-107-112	115-109		127-110
64	113-105-107	113-109		127-122

Section II

4968 Dup of 4954. at 20. Atmos
67
64

4968	484	463	483	479	477	479	461	462	467	458
67	482	463	485	480	477	482	463	463	467	457
64	451	453	462	456	451	450	466	433	438	428

Endurance

	63	64	115	116	167	168	219	220	271	272
4968	433	452	430	414	387	367	343	373	328	315
67	489	455	433	415	387	359	340	367	316	300
64	424	433	423	398	377	357	333	367	319	312

4968
67
64

CD

4968
67
64

4968
67
64

Calipers

	Original	After 1st Run	Before Endurance	after 272 Runs
4973	114-110-112	114-108		122-114
71	115-110-105	118-112		130-115
70	113-108-109	118-114		125-108

Section II.

4973 | Dup of 4954 at 40 Atmos
71 |
70 |

4973	490	488	500	497	500	499	486	475	484	467
71	486	487	497	492	495	483	473	477	464	475
70	508	494	507	500	504	504	491	498	500	492

Endurance

	63	64	115	116	167	168	219	220	271	272
4973	467	492	497	475	471	443	431	455	416	411
71	467	488	477	452	436	400	381	403	367	357
70	492	507	508	482	474	442	428	457	406	398

4973										
71										
70										

4973										
71										
70										

4973										
71										
70										

Calipers

	Original	after 1st Run	Before Endurance	After 272 Runs
4977	109-105-108	112-103		128-113
76	110-107-108	116-107		125-120
74	110-108-108	116-110		130-115

Section II

4977 | Disk of 4954 at 80 atmos
76
74

4977	503	507	513	508	511	513	498	500	497		
76	513	488	500	489	492	497	498	490	482		
74	458	450	442	428	422	418	408	400	413	393	

Endurance

	62	63	114	115	167	168	219	220	271	272
4977	499	502	513	500	500	470	461	430	447	442
76	483	500	500	485	483	450	438	457	421	417
74	398	420	400	387	377	353	338	347	328	325

4977
76
74

CD

4977
76
74

4977
76
74

Calipers

	Original	after 1st Run	Before Endurance	422 mu mm
4982	102-101-102	106-105		124-116
81	102-100-101	112-104		120-115
80	104-102-103	108-102		126-100

Section II

4982 Dup of 4954 at 160 atmos

81

80

4982	507	496	513	511	517	511	507	505	517	503	
81	498	496	510	508	508	508	498	494	509	498	
80	522	513	527	521	525	527	513	513	526	513	

Erdurgel

	63	64	115	116	167	168	219	220	271	272
4982	512	514	512	512	537	487	479	510	474	474
81	500	520	523	512	517	487	493	498	467	467
80	576	533	523	518	553	500	500	514	481	481

	323	324	375	376	427	428	524	530	0	631
4982	430	400	452	442	380	378	325	328	304 Tube Type	253
81	417	423	446	431	367	350	317	367		253
80	440	427	452	441	367	350	333	367		217

632

4982	242										
81	230										
80	233										

4982											
81											
80											

Calipers

	Original	After 1st Run	Before Endurance
4987	93-102-107	103-110	108-110
86	93-101-105	98-102	106-106
84	93-104-104	101-105	104-106

Section #5

4987 | 5 Rej Mi Retrieved perforations
86 | 2 1/0 Containing 5 gms. Citrate
84 | Potash

Chged. 15 hrs @ 200 Discharged @ 100

4987	467	497	499	583	484	496				
86	474	508	572	573	497	505				
84	472	499	506	584	492	500				

Endurance

	54	60	114	112	163	164	215	216	267	268
4987	497	573	517	497	483	449	428	452	406	406
86	573	540	548	527	525	492	481	500	452	459
84	515	527	527	510	507	470	467	467	418	417

	319	320	371	372	423	424	525	526		627
4987	305	327	350	323	343	332	313	267	Not Tested	182
86	392	397	404	343	300	347	373	367		223
84	333	352	333	373	344	328	333	333		183

	628									
4987	205									
86	230									
84	222									

Calipers

	Original	After 1st Run	Before Endurance
5030	91-103-105	100-106	103-108
29	91-102-103	100-105	102-107
28	90-100-102	98-105	102-107

Section I

5030 5 Reg. Mix. Reversed Perforations
29 2 1/2% Containing 2 grammes of
28 Glucose in each cell
Clyd. 15 hrs @ 20.0 discharged @ 10.0
Solution Red.

5030	407	459	486	490	502	507					
29	387	452	483	483	500	514					
28	383	439	471	468	494	500					

Endurance

	59	60	111	112	163	164	215	216	267	268	
5030	492	500	503	475	466	446	420	400	354	322	
29	507	527	541	518	522	498	472	461	440		440
28	496	513	527	500	483	450	433	425	400	393	

	319	320	371	372	423	424	525	526		627
5030	267	247	270	250	184	188	142	163		106
29	380	392	397	384	295	272	197	209		208
28	332	327	310	295	183	196	147	157		145

Broke on 5th Perf. Right Hand

	628
5030	153
29	178
28	148

Calipers

	Original	After 1st Run	Before Endurance
5035	91-103-103	99-105	103-107
34	90-101-103	98-103	103-107
33	90-103-104	99-105	104-107

Section II

5035 | 5 Reg in Reversed Perforations 21%
34 | The Solution contains 2 grammes
33 | of filter paper in each cell. cut
about 1/8" square Chgd 15 hrs 200 Duty @ 100

	60										
5035	502	503	510	496	515	517	493				
34	488	490	493	491	499	500	483				
33	505	510	516	503	521	518	497				

Endurance

	60	61	112	113	164	165	216	217	268	269
5035	492	506	498	481	462	433	417	400	357	345
34	478	492	490	472	447	424	396	389	357	345
33	491	505	492	472	462	432	400	395	353	340

	320	321	372	373	424	425	526	527		628
5035	233	235	267	247	182	182	158	133	Back to 194	160
34	267	267	263	233	376	262	217	232		127
33	233	233	253	233	314	216	258	200		103

	629									
5035	195									
34	147									
33	57									

Calipers

	Original	after 1st Run	Before Endurance
5041	91-101-101	98-107	104-105
40	91-104-101	100-107	102-105
38	90-100-103	98-104	103-104

Section

5041 | 5 Reg Mi Rivered Perforations 2.190
40 | Containing 2 grammes Acetone
38 | in each cell
Obs'd. i 65 hrs @ 7.00 Discharged @ 1.00
5.038 - Solution Yellow & flocculant

5041	196	315	383	432	473	465						
40	117	255	320	398	380	433						
38	198	323	387	440	445	467						

Endurance

	59	60	111	112	163	164	215	216	267	268
5041	422	445	350	422	200	192	166	200	295	160
40	395	428	333	395	298	372	325	267	300	191
38	423	443	367	427	377	300	289	80	225	167

	319	320	371	372	423	424	525	526		627
5041	117	117	120	115	50	67	20	26	Final Thick	7
40	215	167	167	133	100	104	85	90	Now Thick	85
38	156	150	156	147	120	127	97	113		122

	628									
5041	43									
40	117									
38	152									

Calipers

	Original	after 1st Run	Before Endurance
5045	95-103-104	[illegible]	103-104
44	95-106-106		106-107
43	89-100-102		99-100

Section II

5045 | 5 Rep Mis Removed. Perforations 2 1/2
44 | Containing 2 grms Hypophonous
43 | Potash
Chgd 15 hrs @ 2:00. Dischgd @ 1:00

5045	458	489	485	497	490	490						
44	438	491	482	487	485	492						
43	437	471	462	476	470	478						

Endurance

	59	60	111	112	163	164	215	216	267	268
5045	575	520	520	494	516	480	475	487	433	443
44	524	523	498	492	517	495	480	462	445	452
43	498	500	467	472	483	452	444	431	410	408

	319	320	371	372	423	424	525	526		627
5045	383	400	383	383	319	316	273	276	Broken Hole from Top	172
44	390	400	392	383	343	296	267	278		222
43	347	350	350	333	257	245	197	172		93

	628									
5045	225									
44	233									
43	100									

Calipers

	Original	after 1½ Run	Before Endurance
5052	92 - 102 - 104	102 - 104	108 - 106
51	91 - 102 - 103	100 - 104	105 - 106
50	91 - 101 - 103	101 - 104	104 - 106

Section II

5052 | 5 Reg Ni. Removed Perforations 210/0
51 | Containing 3 gms precipitated
50 | (fish) Carbonate of Lime
Clyd 15 hrs @ 1200 Discharged @ 1100

5052	490	498	513	500	498	505	500			
51	487	494	507	492	494	497	498			
50	487	497	508	508	493	499	500			

Endurance

	60	61	112	113	164	165	216	217	268	269
5052	506	510	497	481	500	473	457	429	400	374
51	498	498	467	467	483	448	440	423	367	357
50	506	513	500	482	516	477	468	441	400	384

	320	321	372	373	424	425	526	527		628
5052	333	242	257	223	233	222	132	153	Broke 1:30 Nov 10th	158
51	275	297	252	220	215	205	127	151		158
50	283	303	287	267	247	233	140	207		180

	629
5052	178
51	180
50	206

Calipers

	Original	After 1st Run	Before Endurance
5057	92-103-104	101-105	108 - 105
56	92-105-104	103-106	108 - 107
54	92-105-105	101-106	110 - 109

Section II S

5057 | 5 Reg Nis Pressed Perforations in
56 | 21% Containing 2 grammes of
54 | freshly precipitated carbonate
of Barium
Chgd. 15 hrs @ 200 Discharged @ 100

5057	496	503	582	508	586	500	500	517	570	500	
56	494	503	572	577	507	497	500	531	512	500	
54	493	506	517	514	507	500	500	531	514	507	

Endurance

	63	64	115	116	167	168	219	220	271	272
5057	495	497	522	508	483	472	467	456	423	425
56	493	493	523	510	488	460	461	454	429	424
54	492	495	523	498	487	472	462	455	429	434

	323	324	375	376	427	428	529	530		631
5057	413	417	408	389	347	317	267	252	Broke Tape	260
56	398	393	370	357	317	273	500	225		213
54	377	367	388	376	333	300	223	225		225

	632
5057	247
56	227
54	217

Calipers

	Original	After 1st Run	Before Endurance
5062	92-103-106	101-106	110-107
60	100-112-112	110-113	114-114
59	99-110-113	110-115	113-115

Section II

5062 | 5% Rey Nichols Reversed Perforations in
60 | 21% containing 2 grammes
59 | freshly precipitated Carbonate
Magnesia Chyd 15 hrs @ 200 dischyl @ 100.

5062	483	486	493	492	489	485	492	573	495	485
60	533	547	554	558	555	549	580	577	558	550
59	532	543	552	546	545	533	550	558	545	537

Endurance

	63	64	115	116	167	168	219	220	271	272
5062	494	496	517	500	495	455	448	438	407	397
60	550	557	575	557	538	533	507	505	488	481
59	526	523	557	528	487	474	433	440	400	389

	323	324	375	376	427	428	529	530		631
5062	373	367	332	375	270	343	200	218	1-2	208
60	450	447	408	400	333	374	294	243	2-3	260
59	390	377	267	232	217	201	167	165	3-4	199

632

5062	327										
60	267										
59	223										

Calipers

	Original	After 1st Run	Before Endurance
5066	93-105-104	101-106	108-107
65	95-106-106	103-107	105-105
64	91-104-101	98-106	104-105

Section II

5066 5 Reg Michels Reversed Perforations
65 in 2170 Containing ~ grammes
64 Magnesia Hydroxide
Chgd 15 lbs @ ~00 Dischg'd 100

5066	482	493	505	499	488	495	498			
65	482	487	500	497	490	497	498			
64	488	494	513	492	495	505	503			

Endurance

	60	61	112	113	164	165	216	~17	268	269
5066	483	492	497	503	465	442	412	400	367	355
65	497	501	518	517	507	477	459	454	428	430
64	501	514	533	520	508	482	466	457	433	438

	320	321	372	373	424	425	476	527		628
5066	277	281	245	233	216	207	200	~17	5 Reg Mich Rev Perf	~17
65	390	397	372	353	307	283	257	250		~47
64	390	393	349	325	283	257	257	250		~49

	629
5066	~23
65	~57
64	~53

Calipers

	Original	after 1st Run	Before Endurance	426 ± mm
5092	102-101-100	111-9.8	114-107	124-113
91	102-100-99	112-100	112-107	123-109
90	100-99-100	112-96	112-104	125-113

Section II 9

5092 5 Nichols brg, Corrugations
91 Corrugated 200 Atmos in 21 0/0
90 Chgd, 5 hrs @ 200 Discharged @ 100

5092	506	517	525	529	518	515	518	503			
91	510	521	531	533	527	518	517	517			
90	600	574	533	571	533	525	528	524			

Endurance

	61	62	113	114	165	166	217	218	269	270
5092	587	578	555	528	523	490	506	498	475	477
91	576	533	507	547	552	520	522	500	486	489
90	530	532	585	555	565	517	522	500	486	489

	321	322	373	374	425	426	567	578		630
5092	442	447	443	433	417	393	367	358	345	
91	450	453	462	455	439	417	433	422	378	
90	450	453	443	438	416	400	417	412	360	

	630									
5092	327									
91	358									
90	332									

Calipers

	Original	After 1st Run	Before Endurance	420 ± mm
5095	99-99-98	111-100	109-109	123-114
94	101-98-100	108-100	110-107	121-113
93	101-98-100	109-98	108-107	118-105

Section II

5095 Drop of 5092 in 21.870
94 Except 250 Atmos
93 Chg'd 15 lbs @ 200 Dischg'd 100

5095	482	529	532	538	531	523	528	520		
94	446	464	526	537	531	526	527	523		
93	467	512	537	526	537	531	532	528		

Endurance

	61	62	113	114	165	166	217	218	269	270
5095	522	533	577	547	554	521	517	504	487	492
94	524	527	567	545	555	525	512	503	492	497
93	528	538	592	557	588	547	533	513	498	508

	321	322	373	374	425	426	527	528		629
5095	467	450	467	463	447	431	418	410	5095 Top Wt.	367
94	477	477	482	478	458	445	410	412	94 Top Wt.	367
93	489	487	479	473	456	439	447	463	93 Top Wt.	435

	630									
5095	356									
94	472									
93	448									

Calipers

	Original	After 1st Run	Before Endurance	420th run
5100	102-102-97	110-100	114-101	119-110
5099	98-97-97	107-96	109-106	120-113
98	98-96-97	107-92	104-103	120-112

Section II

5100 Dup of 5099 in 2190.
5099 Except 300 Atmos
98 Chg'd 15 hrs @ 200 Discharged @ 100

5100	462	506	531	537	530	522	515	522			
5099	337	377	471	540	533	522	525	522			
98	475	521	537	542	533	527	528	523			

Endurance

	61	62	113	114	165	166	217	218	269	270
5100	519	523	577	548	567	520	525	509	490	500
5099	578	520	580	550	556	518	505	500	490	497
98	527	533	578	557	563	519	517	509	490	498

	321	322	373	374	425	426	477	528		629
5100	475	483	493	487	465	447	443	445		450
5099	460	450	475	447	425	405	397	397	Pump Shut Down	427
98	467	467	480	475	457	439	397	408		420

	630									
5100	450									
5099	447									
98	433									

Calipers

	Original	after 1st Run	Before Endurance
5177	93-103-105	104-103	109-108
76	97-108-105	103-108	111-110
75	94-105-104	105-106	107-107

Section # 6

5177 | 5 Reg Nichols run in 25%
76 | Solution of Sodium Hydroxide
75 | made from metallic Sodium
by JWA. Solution only to be used
if free from Aluminia
Clyd 15 hrs @ 200 Discharged @ 100

177	543	553	546	537	537	527					
76	543	557	550	543	537	532					
75	552	560	552	543	537	537					

Endurance

	59	60	111	112	163	164	215	216	267	268
5177	462	493	433	500	358	433	306	317	242	217
76	462	485	433	500	373	393	345	353	282	262
75	485	517	493	527	438	448	395	414	367	341

	319	320	371	372	423	424	525	526		627
5177	217	200	197	180	179	167	163	160	Back up to 1000 Kgs	150
76	233	217	197	183	178	171	160	163		153
75	315	292	232	232	217	203	200	200		198

	628
5177	153
76	180
75	227

Calipers

	Original	after 1st Run	Before Endurance
52 19	93-103-106	103-108	105-107
18	91-104-104	100-105	101-104
17	92-104-105	102-106	103-104

Section II 5

52 19 | 5 Rey Jr in 2.0% containing
18 | 3 grammes of Crystals in each
17 | cell of Barium Hydrate
Glyd 15 hrs @ 200 Dried at @ 100

52 19	497	500	496	502	500						
18	499	585	497	497	500						
17	499	576	499	507	508						

Endurance

	58	59	110	111	162	163	214	215	266	267
52 19	497	509	520	513	485	462	445	438	411	413
18	496	505	518	512	486	462	445	438	409	410
17	600	512	517	512	490	475	445	438	408	409

	318	319	370	371	422	423	534	535		626
52 19	353	362	347	333	267	252	255	242	1/2 Load	228
18	349	351	333	322	265	247	237	233		217
17	348	347	313	300	262	246	237	235		229

	627									
52 19	243									
18	220									
17	243									

Calipers

	Original	after 1st Run	Before Endurance
5229	93-105-105	98-104	103-104
28	93-106-104	97-103	108-105
27	92-103-103	98-107	104-108

Section II

5229 | 5 Reg mice on a 10% 28 | containing 1 gramme Stannate 27 | of an alkali + 500 Milligrams aluminium (Aluminium was left out) dyd. 15 hrs @ 200 Dried @ 100

5229	509	518	514	517	514	514				
28	507	518	515	514	513	513				
27	507	517	516	514	512	512				

Endurance

	59	60	111	112	163	164	215	216	267	268
5229	500	528	525	S.C.	492	467	445	442	421	422
28	502	508	523	517	486	467	433	427	409	412
27	500	515	533	520	58[illegible]	462	432	463	443	451

	319	320	371	372	423	424	527	528		627
5229	382	383	360	367	305	283	257	252	Trach. 21 st Rep. Myel.	227
28	347	351	323	310	272	249	222	215		205
27	405	400	392	391	356	333	300	295		250

	628
5229	228
28	222
27	252

Calipers

	Original	After 1st Run	Before Endurance
5234	99-102-103	98-104	107-107
33	92-100-105	99-102	103-103
32	90-101-104	98-105	105-106

Section II

5234 | 5 Reg Mix 21.9% Containing
33 | 2gr ammon. Flouride of Potash
32 | or soda
Note - 400 milligms K Flouride to cell
chgd 15 hrs @ 200 Discharged @ 100

5234	507	508	510	507	550	526	527					
33	507	509	512	517	541	525	525					
32	506	508	509	515	537	518	515					

Endurance

	60	61	112	113	164	165	216	217	268	269
5234	507	517	533	520	522	475	490	446	440	446
33	507	516	533	518	522	467	490	446	442	456
32	485	498	517	505	492	467	440	410	400	408

	320	321	372	373	424	425	526	527		628
5234	395	393	375	379	367	377	307	310		177
33	367	380	351	350	307	313	300	197		197
32	343	347	320	317	108	233	70	130		167

	629
5234	210
33	187
32	212

Sections "I & II Index.

Acetone 5041-38
Alcohol 4767-65
Aluminium 4461-58. 5229-27.
Anode Irons 4921-19.
Anode Ni & Cathodes Irons Inch 4700 4698
Ammonia 4682-80

Barium 5057-54. 5219-17

Cadmium Plated Cups 4531-29
C Cups 4900-4896. 4903-01
Copper Plated Cups 4536-34
Corrugations 5 To inch 4958-54.
4963-60, 4968-64, 4973-70,
4977-74, 4982-80, 5092-90,
5095-93, 5100-5098,
Cups 5000 hi-lex 4909-07, 4914-11
Concave & Convex Pockets Iron, 4589-87
4592-90.
Cups cleaned by Emery Paper 4777-75.

Filter Paper 4482-80, 4485-83, 5035-33

Gelatin 4885-82
Glucose 5030-28
Graphite Iron 4061C-A

Iron without mercury hot
33% 4603-01.
Iron without mercury 4596-94
Iron Plating 4822-21

Lime Carbonate 5052-50

Magnesia Hydroxide 4816-12, 5066-64.
Magnesium Carbonate 5062-59
Mercury a. Zinc 4668-65.
Mercuric Oxide 4485-83

Nickels alkyd hot 32% 4337-85
4291-89, 4376-94
Nickels green hydrate Reversed
Perforations hot 32% 4406-04
Nickels Pockets 3% grid 4878-76
Nickel Pockets reversed perforation
Plated heavy 4850-48.
Nickel Pockets Reversed Perforations
33% 4060-F-A
Nickel Pockets Rev Perf 21% 4112-10
Nickel Pockets Rev Perf hot 33% 4421-19
Nickel Pockets Rev Perf hot 21% 4426-24
Nickel Pockets Rev Perf hot 5% 4734-32
Nickels soaked free of
K.O.H. 4840-38

Nickels soaked in KOH 4266-64
4361-59, 4416-14
Nickel Sulphate 4664-60
Nickels treated with out
Rubber 4356-54.
Nickels Reversed hot 4724-22
4199-97

Potassium Carbonate 4627-25, 4633-31, 4638-34
" Citrate 4487-84.
" Cyanate 4428-34.
" Cyanide 4465-63
" Fluoride 5234-32
" Hypophosphorous 5045-43
" Sulphate 4427-25

Rubber treatment 4804-02, 4809-07
4855½-51, 4859-57, 4864-62.

Silver plated cups 4526-24
Sodium Hydroxide 21% 5177-75.
" Hyposulphite 4470-68
" Silicate 4213-09
Stannate of K or Na? 5229-27.
Sugar 4948-46.

Calipers

	Original	After 1st Run	Before Endurance
5238	93 - 104 - 104	97 - 103	105 - 108
37½	92 - 105 - 105	95 - 104	106 - 106
37	92 - 103 - 107	98 - 103	102 - 105

III

5238 | 5 Req'ts in 2.0% Solution from
37½ | Stock Potash which had
37 | been purified by Lime treated
of Barium
Oxyd. 15 hrs @ 200 Fuchy @ 100

5238	515	515	523	525	500	497	507	507					
37½	510	520	517	518	492	487	497	497					
37	508	518	514	513	492	488	497	497					

Endurance

	61	62	113	114	165	166	217	218	269	270
5238	520	517	517	507	500	457	458	427	387	396
37½	527	500	518	507	500	457	467	433	387	396
37	519	508	527	517	510	455	478	433	418	433

	321	322	373	374	425	426	527	528		629	630
5238	330	347	300	300	267	267	231	239	5 hrs Fuchy @ 100	222	233
37½	343	350	300	300	267	267	247	220		222	233
37	367	367	353	357	310	317	247	244	20 hrs Fuchy @ 100	238	253

5238													
37½													
37													

Calipers

	Original	After 1st Run	Before Endurance
5243	91-104-105	101-107	105-107
42	92-102-104	100-107	108-109
41	92-105-105	101-107	108-109

Fit

5243 5 Reg Mix 2 1/2 o. Containing 4 & C
42 4 of Peroxide of Hydrogen
41 Chyd 15 hrs @ 200 Stachyd @ 100

5243	507	526	518	533	512	517	513				
42	499	527	517	533	517	520	519				
41	490	498	517	523	505	507	508				

Endurance

	60	61	112	113	164	165	216	217	268	269
5243	433	519	540	500	547	467	473	433	442	423
42	525	517	533	493	521	460	467	421	433	423
41	525	508	528	490	517	450	458	424	428	404

	320	321	372	373	424	425	526	527	628
5243	386	387	367	355	343	317	198	195	223
42	358	357	319	290	267	233	50	57	120
41	347	352	333	317	321	297	217	208	212

Pencil Mark 3/4

	629
5243	233
42	87
41	227

Calipers

	Original	after 12th Run	Before Endurance
5263	93-104-105		100-106
62	95-106-106		102-108
61	94-106-105		104-108

5263 5 Ni 2.10.0 which have been
62 heated to 750 with 5 grammes of
61 powdered green nickel hydroxide
for 5 or 6 hrs then solution cooled & poured
off into cells.
Chgd 15 hrs @ 200 Discharged @ 100

5263	492	475	483	488	477	
62	500	494	500	508	498	
61	496	487	497	504	494	

Endurance

	58	59	110	111	162	163	214	215	266	267
5263	500	490	518	470	496	442	467	433	410	422
62	525	500	533	500	543	470	488	450	501	423
61	527	570	528	500	521	467	490	445	428	433

	318	319	370	371	422	423	474	475		526
5263	375	382	353	348	310	312	216	223	Probably not	178
62	367	382	333	333	281	267	243	223		133
61	393	387	350	342	317	312	263	257		193

	527
5263	198
62	143
61	207

Calipers

	Original	After 1st Run	Before Endurance
53 25	96-108-105	104-110	107-108
24	98-102-102	94-103	95-102
23	90-107-105	95-105	103-105

III

325 5 Ry Wi - 2190 made from Sump
24 Potash and not treated with Barium
23 Chgd 15 hrs @ 200 Discharged @ 100

53 25	467	491	473	483	479	
24	477	493	480	487	487	
23	477	499	477	491	487	

Endurance

	58	59	110	111	162	163	214	215	266	267
53 25	477	447	508	473	492	442	437	400	397	385
24	494	463	505	477	497	447	457	420	419	422
23	528	498	527	490	509	454	448	410	392	400

	318	319	370	371	422	423	524	525		626
53 25	350	353	318	300	320	297	231	212		187
24	367	367	366	355	357	358	358	345	Permanent Set	195
23	357	358	318	307	320	300	252	233		200

	627
53 25	209
24	218
23	223

Calipers

	Original	After 1st Run	Before Endurance
5379	92-105-103	98-103	101-104
78	94-104-102	99-102	102-104
77	10-104-102	99-105	105-105

5379 | 5 Reg Nit 2% + 2 cc of
78 | strong Ammonia in solution
77 | Chgd 1.5 hrs @ 200 Discharged @ 1.00

5379	455	463	478									
78	453	481	475									
77	454	481	478									

Endurance

	56	57	108	109	160	161	212	213	264	265
5379	563	528	552	512	547	480	488	445	452	447
78	533	519	545	512	542	496	510	467	483	489
77	525	515	533	500	551	491	500	455	50	433

	316	317	368	369	420	421	472	473		624
5379	383	386	359	348	361	333	287	252	210 Pull Thru	215
78	419	433	430	420	413	403	312	300		272
77	388	396	392	367	367	362	258	233		200

	625
5379	238
78	252
77	203

Calipers

	Original	After 1st Run	Before Endurance
5477	102-97-95		132-114
76	99-97-98		128-118
74	101-98-97		134-117

5477 5 Mi Big Corrugations Reversed
76 Perforations 200 Atmos
74 Charged & Leached in 33%
Charged 16 hrs @ 200 Leached @ 100

5477	453	507	567									
76	452	507	572									
74	452	495	539									

Endurance

	56	57	108	109	160	161	212	213	264	265
5477	578	567	518	533	452	480	363	382	292	323
76	532	577	495	548	492	500	333	400	318	361
74	528	575	495	533	418	451	381	378	306	333

	316	317	368	369	420	421	522	523		624
5477	265	267	245	238	233	220	227	232	Break in Mill Run	160
76	288	292	267	267	263	267	253	267		200
74	297	286	253	267	257	260	220	217		155

	625
5477	195
76	209
74	173

Calipers

	Original	After 1st Run	Before Endurance
54/81	99-97-95		123-108
80	101-95-97		122-117
79	99-96-92		125-109

54/81 Dup of 5477 Except at
80 @ 250 Atmos
79 Clyd 15 hrs @ 200 Dischyd @ 100

54/81	478	520	545									
80	440	498	527									
79	447	473	522									

Endurance

	56	57	108	109	160	161	212	213	264	265
54/81	552	627	567	613	520	567	488	510	387	500
80	570	566	520	533	484	500	437	465	395	446
79	488	550	500	542	448	487	394	433	307	342

	316	317	368	369	420	421	522	523		624
54/81	363	354	300	300	297	290	300	340	Very Very Small	257
80	365	353	295	292	290	281	277	252		213
79	300	292	267	260	258	248	232	240		188

625

54/81	270									
80	245									
79	198									

Calipers

	Original	After 1st Run	Before Endurance
5486	96-92-92		116-101
85	94-92-90		113-105
84	95-92-95		118-106

5486 Dup of 5477
85 Except @ 300 atmos
84 Aged 15 hrs @ 200 Scratched @ 100

5486	456	497	530									
85	460	512	573									
84	447	497	527									

Endurance

	56	57	108	109	160	161	212	213	264	265
5486	571	553	530	550	515	523	513	485	427	477
85	547	537	538	613	495	558	467	467	477	433
84	518	533	523	533	510	520	517	500	451	88

	316	317	368	369	420	421	522	523			624
5486	413	411	348	350	380	344	265	297	278		
85	337	327	285	288	267	267	247	238	208		
84	421	433	367	394	357	367	300	320	270		

	625
5486	308
85	278
84	300

Calipers

	Original	After Ct. Run	Before Endurance
5491	92-105-102	102-106	10.5-10.5
90	96-108-105	104-107	107-103
89	92-104-104	99-105	106-105

491 5 Reg Wi 2170. containing
90 3 gms Borax
89 Chy 4 15 hrs @ 200 Dried 4 @ 100

5491	477	493	503	510	505	
90	467	493	487	500	495	
89	450	490	496	495	490	

Endurance

	58	59	110	111	162	163	214	215	266	267
5491	533	522	545	512	537	487	487	448	467	462
90	535	514	542	520	537	482	482	444	449	445
89	521	510	540	500	98	478	467	433	433	433

	318	319	370	371	422	423	574	575		626
5491	392	400	383	367	364	350	265	347	Broke Spring	225
90	383	391	373	363	360	351	283	256		233
89	367	367	347	325	320	296	283	224		197

	627									
5491	237									
90	250									
89	210									

Calipers

	Original	after 1st Run	Before Endurance
5522	93-105-103	103-108	104-103
21	91-103-104	100-104	101-102
20	91-104-104	101-106	103-107

522 5 Reg Ni 21% containing
21 3 grammes Carborate Strontia
20 in each cell after assembling
rated 10 hrs.
Chgd 15 hrs @ 200 Discharged @ 100

5522	484	485										
21	494	488										
20	487	495										

Endurance

	55	56	107	108	159	160	211	212	263	264
5522	533	518	545	507	533	487	492	447	415	462
21	537	533	542	510	533	482	483	450	467	462
20	533	527	547	510	544	483	483	440	458	455

	315	316	367	368	419	420	521	522		623
5522	387	385	347	347	364	333	273	248	Taken out Accidentally	228
21	390	400	377	364	364	371	297	265		225
20	391	397	388	364	367	348	387	260		233

	624									
5522	243									
21	245									
20	252									

Calipers

	Original	After 1st Run	Before Endurance
5526	92-104-105	103-107	105-108
24	94-103-106	102-107	104-106
23	90-105-105	100-106	98-104

5526 5 Reg Mi 7.1% Containing 3 grammes
24 Carbonate Cerium Each Cell
23 After assembling rested 10 hrs.
Chgd 15 hrs @ 200 Discha'd @ 100

5526	490	486										
24	485	491										
23	495	491										

Endurance

	55	56	107	109	159	160	211	212	263	264
5526	542	510	540	500	533	481	475	443	457	453
24	527	513	525	488	508	467	472	433	438	433
23	522	505	500	483	497	452	447	411	418	419

	315	316	367	368	419	420	521	522		623
26	382	388	386	363	355	333	332	322	Bad Mix	182
24	367	379	377	362	343	327	332	312		193
23	362	367	357	333	317	295	190	192		115

	624								
26	200								
24	203								
23	132								

Calipers

	Original	After 1st Run	Before Endurance
5562	93-104-104	102-106	104-105
61	92-103-104	102-104	103-104
60	93-106-105	98-107	102-105

5562 5 Reyn soaked, 6 hrs in hasp
61 print grain Alcohol on hub
60 plate @ about 125°F Then
Assembled with irons in 21%
dry'd 15 hrs @ 200 Brichy'd @ 100

5562	467	482	494	498	497	503	506				
61	477	490	495	500	500	507	508				
60	464	477	494	493	496	500	505				

Endurance

	60	61	112	113	164	165	216	217	268	269
5562	543	523	547	513	542	491	500	462	465	487
61	552	529	550	517	521	490	500	465	466	487
60	547	522	552	517	550	500	500	462	467	488

	320	321	372	373	424	425	526	527	Brush in Pan	Rest Wash	629
5562	400	410	405	389	383	355	150	147			248
61	390	394	387	362	378	347	258	248			272
60	407	415	423	410	400	338	317	313			238

	629
5562	237
61	230
60	260

Calipers

	Original	After 1st Run	Before Endurance
5582	94-105-104	106-105	101-105
81	94-106-104	101-103	102-107
80	96-102-108	104-108	106-109

5582 5. Reg mi 2.0% containing
81 2 grams Antimoniate of Potash
80 or sodium (400 mily each cell).
Chg'd 15 hrs @ 200 Drachyl @ 100

5582	463	407	498	487	502	
81	458	507	497	483	500	
80	463	504	482	482	492	

Endurance

	58	59	110	111	162	163	214	215	266	267
5582	537	514	525	500	500	459	447	420	385	400
81	531	513	542	500	523	473	470	448	405	433
80	547	513	6715	508	547	487	484	447	413	444

	318	319	370	371	422	423	526	527	Trouble 2 Cells	626
5582	347	349	333	315	333	293	263	242		207
81	367	367	358	345	353	319	276	253		223
80	367	377	352	383	346	318	284	253		195

	627
5582	233
81	242
80	227

Dalapon

	Original	After 1st Run	After 2nd Endurance
55-85	93-103-103	100-103	103-105
84	90-100-99	99-100	101-102
83	100-101-99	95-100	100-102

55-85 5 Rey Ni 2170 with 5 grammes
84 powdered Lead Glass through
83 150 mesh or nearest thereto made by Dalby (5 grammes to each cell)
chyd 1.5 hrs @ 200 Dechyd @ 100

55-85	477	485	500	496							
84	467	480	491	488							
83	467	482	483	495							

Endurance

	57	58	109	110	161	162	213	214	265	266
55-85	536	517	557	500	500	450	450	400	367	348
84	503	482	500	457	442	400	377	345	300	257
83	533	510	550	500	507	460	457	390	358	314

	317	318	369	370	421	422	473	474	Finely ground 1 hr	625
55-85	184	182	77	90	43	27	15	15		2
84	122	119	40	38	35	13	3	3		0
83	172	178	78	73	45	20	10	6		0

	626									
55-85	2									
84	0									
83	0									

Calipers

	Original	After 1st Run	Before Endurance
5591	97-107-108	103-106	107-107
90	96-107-106	103-106	107+106
89	96-105-106	103-106	102+106

5591 | 5 Ni in 21% Containing 1 gramme
90 | Silenate of Potash or Soda per
89 | cell
Chgd 15 hrs @ 200 Discha @ 100

5591	418	475	474	473								
90	493	492	482	485								
89	442	487	481	478								

Endurance

	57	58	109	110	161	162	213	214	265	266
91	552	515	520	487	493	453	465	422	387	377
90	592	541	550	508	514	488	493	410	433	400
89	582	527	547	500	513	479	493	440	438	428

	317	318	369	370	421	422	473	474		525
91	323	315	253	233	265	228	185	148	Readings taken April 2	133
90	362	354	267	252	287	257	195	193		200
89	376	381	273	300	285	237	173	160		200

	626
91	143
90	207
89	206

Calipers

	Original	After 1st Run	Before Endurance
5595	95-103-106	100-107	102-103
94	97-107-104	102-107	103-107
93	96-105-107	101-104	104-105

5595 5 Ray Ni 21% Containing
94 1 gramme Tellurate of Potassium
93 or Sodium per cell
Chg 15 hrs @ 200 Discharged @ 100

5595	464	460	459	458								
94	468	467	466	463								
93	462	456	452	453								

Endurance

	57	58	109	110	161	162	213	214	265	266
5595	539	500	500	473	473	447	490	444	317	463
94	557	515	507	483	467	465	465	448	400	393
93	537	508	497	480	452	451	460	422	383	377

	317	318	369	370	421	422	523	524		625
5595	325	320	233	210	167	143	130	137	Break in	53
94	333	328	233	210	187	157	145	143	Run (pulse)	100
93	319	317	233	200	165	133	145	137		80

	626
5595	48
94	98
93	95

Calipers

	Original	After 1st Run	Before Endurance
5%10	96-106-105	102-105	104-105
09	92-104-106	98-105	102-106
08	94-106-104	103-107	105-106

7610 5 Rey Ni 21% with 2 grams
09 oxalic acid
08 Clyd 15 hrs @200 Dischyd @100
(400 mily Each Cell)

5%10	460	502	488	481									
09	460	507	492	482									
08	460	500	467	484									

Endurance

	57	58	109	110	161	162	213	214	265	266
5%10	527	523	543	507	515	475	490	451	442	418
09	552	523	533	507	515	480	500	464	462	446
08	533	515	530	500	502	473	497	454	448	435

	317	318	369	370	421	422	523	524	575	626
5%10	377	380	347	312	340	295	85	187	255	152
09	400	417	400	343	460	327	257	255	255	200
08	387	397	392	350	367	325	253	224	255	209

	626
5%10	186
09	210
08	237

Calipers

	Original	After 1st Run	Before Endurance
5&6	16	95-107-105	105-108	101-104
	15	90-101-105	100-105	101-105
	14	95-106-105	103-108	106-107

5&6 16 5 Reg ni 210% containing
15 3 grammes Formation of Potash or
14 Rubia
Chyd 15 hrs @ 200 Dicchy'd @ 400
600 Mifg Each. Cell

5&6	16	465	507	503	500							
	15	459	496	485	497							
	14	465	509	505	520							

Endurance

		57	58	109	110	161	162	213	214	265	266	
5&6	16	529	527	533	508	516	489	514	467	462	445	
	15	558	532	533	508	516	488	498	467	450	433	
	14	558	533	543	513	526	482	498	467	462	447	

		317	318	369	370	421	422	523	524	Middle Mid	625	
5&6	16	400	405	400	367	367	322	333	322		193	
	15	388	392	392	350	367	325	353	353		360	
	14	389	392	367	333	367	318	277	360		222	

		626										
5&6	16	188										
	15	254										
	14	215										

Calipers

	Original	After 1st Run	Before Endurance
5-620	90-101-98	94-100	96-100
19	94-105-104	102-107	104-106
18	93-106-106	101-105	104-102

5-620 5 Reg Mi - 21% with 3 grammes
19 Succinic acid free cell
18 Clyd, 15 hrs @ 200 Discharged @ 100

5-620	483	476	482	461								
19	484	485	487	486								
18	483	488	489	490								

Endurance

	57	58	109	110	161	162	213	214	265	266
5-620	S.P.	492	525	490	500	465	485	437	433	490
19	559	531	553	577	530	492	525	480	482	457
18	567	540	550	577	523	495	500	472	462	477

	317	318	369	370	421	422	523	524	625	626
5-620	367	342	400	333	367	340	262	258	Pt. Pulled off	217
19	412	407	425	398	375	312	250	233	Pt. Pulled off	113
18	400	393	386	333	360	305	252	243	Pt. Pulled off	270

	626
5-620	220
19	163
18	238

Calipers

	Original	After 1st Run	Before Endurance
5696	94-105-101	100-105	103-108
95	91-106-104	99-105	102-105
94	94-104-106	101-106	104-108

5696 | 5 Reg Ni 2170 Containing
95 | 1 gram cleaar Tunica powdered
94 | up to 1/8 + smaller to each cell
Chyd. 15 hrs @ 200 Drychyd @ 100

5696	470	482	478	489	490	489							
95	467	480	485	487	490	490							
94	464	478	485	488	490	491							

Endurance

	59	60	111	112-163	164	215	216	267	268
5696	571	573	538	495	502	473	492	443	442	425
95	578	595	515	485	496	458	475	437	483	412
94	538	570	530	498	516	473	498	448	444	433

	319	320	371	372-423	424	525	526			627
5696	388	378	367	343	367	330	178	200		167
95	378	367	359	338	343	297	230	223	Finish Ring Pull Ring	157
94	410	398	400	383	400	353	200	207		193

	628									
5696	165									
95	190									
94	193									

Calipers

	Original	After 10% Run	Before Endurance
5-7-27	99-95-97		109-105
25	100-98-95		115-105
24	100-96-97		114-104

27 5 Michel Big Corrugations 300 Atmos
25 Soaked 6 hrs in grain alcohol
24 Then dried 2 hrs on heater
Run in 2.1% containing 2 grms per cell of Hyponeuphite of soda or Potash
Chgd 15 hrs @ 2.00 Discharged @ 1.00

	50										
5-7-27	0	433	429	506	511	498					
25	0	479	502	506	507	485					
24	0	456	433	511	514	499					

Endurance

	59	60	111	112	163	164	215	216	267	268
5-7-27	555	554	567	543	555	550	560	550	530	513
25	582	575	567	533	561	523	558	520	507	510
24	605	552	570	542	573	533	582	543	542	523

	319	320	371	372	423	424	525	526		627
5-7-27	482	480	478	467	467	443	350	333	Finish 5-7-27 1000 Atmos	357
25	476	475	477	453	440	445	423	412		423
24	487	487	493	477	473	467	442	443		433

	628										
5-7-27	353										
25	414										
24	414										

Calipers

	Original	after 12 hrs	Before Endurance
58 35	92-104-105	104-107	105-105
34	95-106-107	102-103	105-108
31	93-105-106	103-108	104-107

5 Ray ni 210/0 containing
3 grammes Carbonate Ammonia
in each cell
Clyd. 15 hrs @ 200 Dischyd @ 100.

58 35	275	383	432	450	
34	265	383	430	443	
31	289	417	458	477	

Endurance

	57	58	109	110	161	162	213	214	265	266
58 35	574	572	533	498	520	483	492	477	482	454
34	558	527	532	517	532	491	443	447	493	467
31	551	524	543	511	527	487	500	459	482	452

	317	318	369	370	421	422	473	474	525	526
58 35	421	410	423	400	385	363	363	357	Broke 10:10	367
34	427	412	421	397	400	352	353	353		192
31	421	412	420	400	408	367	377	358		252

	626
58 35	233
34	200
31	233

Calipers

	Original	After 1st Run	Before Endurance
58 60	93-106-104	102-105	103-105
59	96-107-100	108-110	104-106
58	93-103-106	107-105	107-103

5 Reg mi 2 1/0 Containing
2 grammes freshly precipitated
carbonate of Magnesia in each cell
chyd 15 hrs @ 200 Dried @ 100

58 60	467	482	476	476	
59	462	475	473	473	
58	457	470	470	468	

Endurance

	57	58	109	110	161	162	213	214	265	266
58 60	549	512	530	493	497	458	477	437	433	410
59	553	517	533	497	513	473	497	453	443	427
58	546	510	543	493	507	467	493	440	443	427

	317	318	369	370	421	422	523	524	575
58 60	386	367	353	327	328	297	340	333	167
59	395	387	378	317	367	329	313	300	183
58	397	383	378	348	359	327	300	300	290

Broken Wire

	626
58 60	170
59	200
58	254

Calipers

	Original	after 1st Burn	Before Endurance
5% 65	92-104-104	96-105	101-105
64	89-94-102	96-100	99-100
63	91-103-102	98-103	100-103

5% 65 | 5 Wt 21% Containing
64 | 2 gms Kaolin Each Coll
63 | Clyd 15 hrs @ 200 Dried 4 @ 100

5% 65	493	487	491	495	4
64	493	488	489	494	
63	493	488	486	493	

Endurance

	57	58	109	110	161	162	213	214	265	266
5% 65	486	460	343	317	200	233	167	147	100	100
64	492	457	348	324	248	222	183	167	115	107
63	508	473	395	497	291	300	212	196	134	123

	317	318	369	370	421	422	473	474		525
5% 65	80	85	63	47	33	28	7	7	Probably not 100% hydrated	0
64	90	93	63	47	42	20	8	8		8
63	95	100	67	47	45	23	12	12		5

	526
5% 65	0
64	0
63	3

Calipers

	Original	After 1st Run	Before Endurance
5-9 15	9a 104-106	100-105	99-103
14	94-107-104	105-107	101-106
13	9a 99-105	98-100	96-98

5 ml 21% containing 3 gms
14 freshly precipitated carbonate
3 of Calcium each cell
Aug 15 hrs @ 7.00 Disch/@ 100

5-9 15	.503	502										
14	.498	475										
13	.493	488										

Endurance

	55	56	107	108	159	160	211	212	263	264
5-9 15	543	548	572	530	542	510	543	491	467	450
14	577	539	555	520	532	499	525	472	447	430
13	565	533	553	518	542	500	528	485	482	450

	315	316	367	368	419	420	581	582		623
5-9 15	367	342	347	310	370	297	200	58	Broke in Mon Apl 14	192
14	366	333	333	300	318	300	267	255		173
13	367	360	347	312	373	320	267	267		180

	624									
5-9 15	225									
14	175									
13	215									

Calipers

	Original	After 1st Run	Before Endurance
57 69	93 · 103 - 104	100 - 105	105 - 105
68	92 · 101 - 101	101 - 102	105 - 104
67	93 · 104 - 104	101 - 104	103 - 104

5769 | 5 Rey Mc actually boiled 1 hr
68 | in 1 quart of 1% K.O.H.
67 | Run in 21%.
Chgd 15 Rus @ 200 Discharged @ 100

5769	473	422	500	497								
68	229	490	508	497								
67	464	490	488	492								

Endurance

	57	58	109	110	161	162	213	214	265	266
5769	562	533	542	515	527	492	493	477	445	420
68	533	517	542	513	537	492	520	461	492	482
67	573	537	542	510	527	487	498	467	445	445

	317	318	369	370	421	422	523	524		625
5769	387	365	360	200	373	317	397	263	Final Time Run	183
68	447	441	470	437	440	420	318	380		350
67	387	365	358	333	367	314	285	188		223

	626
5769	138
68	320
67	333

Calipers

	Original	After 1st Run	Before Endurance	421 ± 2 hrs
5993	89-99-101	95-99	97-100	113-110
92	92-102-101	99-104	101-104	119-115
91	97-103-104	101-103	103-105	115-110

5993 5 ml 2190 Containing
92 2.5 miligrams Sulphide of Potassium
91 in each cell
Chgd: 15 hrs @ 2100 Dischgd @ 100

5993	480	490	516									
92	473	494	500									
91	495	495	500									

Endurance

	56	57	108	109	160	161	212	213	264	265
5993	557	532	545	522	540	496	513	492	487	488
92	532	532	542	515	542	495	540	495	492	490
91	553	532	553	528	550	492	542	510	503	510

	316	317	368	369	420	421	522	523		624
5993	462	452	443	438	459	430	378	367	Broke Pin	350
92	461	456	446	417	430	430	395	393		358
91	477	477	483	453	473	457	415	410		397

	625
5993	310
92	352
91	367

Calipers

	Original	After 1st Run	Before Endurance	421st Run
5996	90-102-100	96-104	98-107	114-109
95	94-107-104	101-105	107-105	117-113
94	93-100-103	100-101	102-102	117-111

5996 5 Ni 21% Containing
95 50 Milligrams Sulphided Potassium
94 in each cell
Chgd 15 hrs @ 2.00 Discharged @ 100

5996	477	500	512								
95	477	500	515								
94	467	475	490								

Endurance

	56	57	108	109	160	161	212	213	264	265
5996	561	539	553	528	550	526	527	493	498	492
95	567	545	552	527	560	526	542	468	507	487
94	531	528	535	500	524	498	500	447	485	462

	316	317	368	369	420	421	512	523	0	422
5996	467	443	483	483	457	429	458	387	Previous to Run	363
95	473	454	493	497	462	453	493	413		331
94	450	428	460	470	433	430	383	383		315

	625									
5996	342									
95	329									
94	285									

Calipers

	Original	After 1st Run	Before Endurance	4x1 st. run
6001	90-100-99	96-102	103-103	112-113
00	92-102-100	98-100	101-102	118-111
5999	93-103-104	99-103	102-107	119-118

6001 5 Mi 2170 Continuity
00 125 Milligrams Sulphide of
5999 Potassium in each cell
dyd 15 hrs @ 200 Discharged @ 100°

6001	484	493	492								
00	487	497	500								
5999	495	495	498								

Endurance

	56	57	108	109	160	161	212	213	264	265
6001	531	527	532	512	531	508	498	477	462	452
00	533	527	542	515	533	514	507	490	485	480
5999	548	533	550	527	548	522	517	492	489	487

	316	317	368	369	420	421	472	473		624
					Cap				Average	
6001	422	390	433	483	507	487	433	383	433	323
00	453	433	460	473	420	437	417	410	433	392
5999	462	439	477	490	433	438	423	408	433	356

	625
6001	288
00	363
5999	348

Calipers

	Original After 1st Run	Effect of Endurance	421st min
6006	94-102-104	101-103	103-115
05	92-101-104	95-100	103-104
04	94-100-106	99-99	105-103	120-111

6006 | 5 Ni 21.0 Containing
05 | 2.50 Milligms Sulphide of
04 | Potassium in each cell
Chgd 15 hrs @ 20.0 Dischgd @ 100

6006	482	482	487								
05	483	498	500								
04	482	493	493								

Endurance

	56	57	108	109	160	161	212	213	264	265
6006	527	527	533	509	526	507	507	483	478	478
05	528	532	534	520	525	512	513	487	485	479
04	533	527	533	511	531	507	447	466	479	477

	316	317	368	369	420	421	524	523	Tumbling Mill	624
6006	452	432	483	483	462	450	450	442		433
05	449	428	467	477	437	428	392	382		369
04	449	427	467	467	428	424	392	382		359

	625									
6006	412									
05	338									
04	333									

Calipers

	Original	After 1st Run	Before Endurance	421 ±
60/3	92-103-102	101-103	105-105	124-114
/2	94-104-105	101-105	107-108	117-113
/1	90-102-101	97-102	102-105	115-114

60/3 5 hr 21% Containing
/2 500 Miligrams Sulphide of
/1 Potassium in each cell
Chgd 15 hrs @ 200 Discharged @ 100

60/3	413	493	497								
/2	467	492	497								
/1	480	492	493								

Endurance

	56	57	108	109	160	161	212	213	268	265
60/3	547	537	543	516	531	503	493	470	467	460
/2	567	537	546	508	523	496	492	460	456	437
/1	523	527	526	500	523	498	490	462	471	462

	316	317	368	369	420	421	522	523		624
60/3	426	379	433	425	390	360	315	387	Final Volt	387
/2	467	386	433	400	343	378	346	312		327
/1	432	411	467	478	437	447	407	400		350

625

60/3	341										
/2	312										
/1	343										

Calipers

	Original	After 1st Run	Before Endurance
6018	93-107-104	99-106	101-103
17	93-105-101	100-105	100-102
16	93-102-106	100-104	100-101

6018 5 Reg Ni 21% Containing
17 2 grammes Succinic Acid
16 in each cell.
Chg'd 15 hrs @ 2.00 Discha'd @ 100

6018	432	464									
17	427	447									
16	434	469									

Endurance

	55	56	107	108	159	160	211	212	263	264	
6018	537	500	533	492	517	488	483	442	433	437	
17	517	492	522	480	497	467	445	400	370	350	
16	533	517	533	493	509	475	457	421	429	416	

	315	316	367	368	419	420	521	522		624
6018	390	369	362	350	373	333	88	90	Probably Short	41
17	317	310	280	278	180	168	33	50		28
16	340	333	267	267	120	127	27	38		16

	625									
6018	53									
17	36									
16	33									

Calipers

	Original	After 1st Run	Before Endurance
6038	92-103-103	97-102	101-104
37	94-105-103	100-105	102-104
36	92-106-105	98-106	102-106

6038 5 Reg Ni 210 containing
37 2 grammes Barium Sulphite
36 in each cell.
Chgd 15 hr @ 200 Discharged @ 100

6038	478	483	504	500							
37	478	483	499	497							
36	478	483	498	497							

Endurance

	57	58	109	110	161	162	213	214	265	266
6038	567	532	554	510	519	492	485	458	455	440
37	561	538	551	507	519	492	483	453	455	442
36	552	534	551	511	527	492	486	453	456	428

	317	318	369	370	421	422	523	524	Broke 525	625
6038	400	384	400	400	348	320	377	358	100% Wet	273
37	397	377	396	397	344	322	395	363		294
36	383	380	397	397	347	327	378	358		288

	626
6038	232
37	262
36	249

Calipers

	Original	After 1st Run	Before Endurance
6053	93-103-103	99-103	104-104
52	93-103-105	100-103	103-105
51	94-103-105	102-106	105-105

6053 5 Ni 21% Containing 10 Milligrs
52 Flour of Sulphur in bottom
51 of cell
Chgd 15 hrs @ 200. Discharged @ 100

6053	480	485	503	500	495	495				
52	473	480	497	492	497	495				
51	483	485	510	505	497	495				

Endurance

	59	60	111	112	163	164	215	216	267	268
6053	533	0	531	494	459	457	440	425	408	400
52	537	517	531	494	511	480	460	417	427	413
51	587	537	560	513	531	495	489	418	455	443

	319	320	371	372	423	424	525	526		627
6053	343	323	300	277	263	233	262	247	5.6	
52	393	333	352	73	308	58	253	230	1.75	
51	417	367	361	333	315	285	267	280	2.97	

628

6053	133									
52	200									
51	259									

Calipers

	Original	After 12½ Run	Before Endurance
60	56	98-102-103	98-102	105-10X
	55	93-102-103	100-103	106-106
	54	94-102-105	103-102	105-10X

56 5 Ni 2 10 % Containing
55 30 Milligrms Flow of Sulphur
54 in bottom of cells.
Chg'd 15 hrs @ 200 Discha'd @ 100

60	56	474	487	493	508						
	55	478	493	492	510						
	54	473	487	483	500						

Endurance

		57	58	109	110	161	162	213	214	265	266
60	56	553	531	552	512	533	491	482	447	457	434
	55	563	533	556	513	527	492	467	447	458	427
	54	545	524	538	507	521	492	467	450	437	433

		317	318	369	370	421	422	523	524		625
60	56	384	349	355	397	313	282	345	333	Made with New Wet	254
	55	373	333	333	333	307	278	347	345		245
	54	383	347	361	353	318	283	353	347		262

		626									
60	56	232									
	55	197									
	54	226									

Calipers

	Original	After 1st Run	Before Endurance
6063	94-103-102	99-104	104-104
62	92-99-107	98-106	101-103
61	93-103-102	99-104	104-106

6063 5 Mi 2.1% Containing
62 6.0 Milligrams T-Form of Sulphur
61 in bottom of each cell
Chgd 1.5 hrs @ 200 Discharged @ 100

6063	472	487	487	500								
62	467	486	485	497								
61	467	492	493	500								

Endurance

	57	58	109	110	161	162	213	214	265	266
6063	567	530	550	506	532	492	472	435	428	425
62	550	522	537	497	521	492	467	430	428	416
61	544	522	532	496	512	478	467	428	427	417

	317	318	369	370	421	422	523	524	625	626
6063	393	357	382	348	373	380	353	348	195	120
62	377	346	367	357	325	285	344	228	153	227
61	383	345	365	348	315	280	345	233	118	125

Note Worn Pins

6063												
62												
61												

Calipers

	Original	After 18 Runs	Before Endurance
6066	97-102-102	98-102	100-103
65	97-104-103	99-102	104-104
64	91-100-104	101-105	105-107

6066 5 Mi 21% containing
65 12.0 milligrms. 7 hours of Sulphur
64 in bottom of cells.
Chgd. 15 hrs @ 200 Discharged @ 100

6066	467	489	480	498	
65	473	493	490	508	
64	473	492	490	505	

Endurance

	57	58	109	110	161	162	213	214	265	266
6066	552	524	541	498	508	477	460	423	438	418
65	544	549	525	197	S.C.	515	477	433	S.C.	400
64	567	533	543	506	527	490	472	433	433	418

	317	318	369	370	421	422	473	474	525	526
6066	337	348	392	367	356	300	277	348	Short circuited	293
65	393	347	386	367	355	320	270	270		328
64	390	353	367	357	323	310	277	259		326

	626									
6066	347									
65	278									
64	252									

Calipers

	Original	After 1st Run	Before Endurance	422nd min
7070	92-104-104	101-105	103-106	118-111
69	92-100-104	102-102	104-104	120-117
68	90-101-101	100-103	101-105	112-113

7070 5 Reg Ni 21% Containing
69 nin each cell 100 Milligms
68 of precipitated Ferric hydroxide
Chgd 15 hrs @ 200 Discharged @ 100

7070	487	489	495	500	500						
69	488	486	495	500	500						
68	489	485	491	500	500						

Endurance

	58	59	110	111	162	163	214	215	266	267
7070	570	539	566	523	552	521	530	490	504	500
69	556	533	556	516	546	515	517	482	479	485
68	524	521	542	509	530	497	495	463	477	467

	318	319	370	371	422	423	474	475		526
7070	462	442	495	483	453	447	428	433	Original Thickness	387
69	447	431	467	463	438	447	405	395		398
68	432	411	456	450	398	388	358	333		330

	527
7070	357
69	318
68	300

Calipers

	Original	After 1st Run	Before Sulphurised	422 = mm
7077	91-102-101	100-104	101-105	113-114
76	90-100-102	98-103	104-102	113-110
75	92-102-106	101-107	102-104	116-115

7077 | 5" Rey Nr 210/0 containing
76 | 100 Milligms Ferrous hydroxide
75 | in each cell.
Use Ferrous Sulphate in solution with minimum amount of water to dissolve it + pour into cells making the precipitate in the cell The Sulphuric will do no harm
Clyd 15 hrs @ 200 Dischy @ 100

7077	477	477	497	500							
76	478	491	500	520							
75	467	478	491	497							

	57	58	109	110	161	162	213	214	265	266
7077	532	532	532	500	525	491	492	476	472	467
76	562	539	561	530	562	525	537	500	510	500
75	546	533	497	521	483	485	470	472	530	

	317	318	369	370	421	422	523	524	625	626
7077	438	412	456	447	413	400	351	333	330	300
76	466	443	487	483	458	447	425	403	407	367
75	430	408	455	450	425	412	424	390	397	367

Calipers

	Original	After 1st Run	Before Endurance	420 mμ
7168	92-104-105	99-105	102-105	114-111
67	91-103-103	99-103	100-104	116-117
66	93-104-105	101-106	103-106	113-110

7168 5 Reg Ni 210/0 Containing
67 250 Milligms Antimonate of
66 Potassium or Soda in each cell
Chg'd 15 hrs @ 200 Discharged @ 100

7168	483	489										
67	484	490										
66	484	490										

Endurance

	55	56	107	108	159	160	211	212	263	264
7168	547	529	545	510	543	509	510	430	483	472
67	554	529	561	517	567	520	530	483	505	487
66	532	515	533	499	543	500	507	467	483	478

	315	316	367	369	419	420	521	522		623
7168	448	423	473	477	460	430	428	409	420 mμ	405
67	465	442	494	483	455	446	458	415		382
66	453	431	486	477	433	423	454	396		347

	624											
7168	395											
67	362											
66	338											

Calipers

	Background	After 1st Run	After Endurance
7175	93-105-106	100-106	104-105
74	90-100-101	97-102	99-102
72	90-102-100	97-102	102-103

7175 | 5 Reg Ni 2% Containing
74 | 500 Milligms Antimonate of
72 | Potash or soda in each cell
Chgd 15 hrs @ 200 Discha @ 100

7175	486	508										
74	482	490										
72	482	490										

Endurance

	55	56	107	108	159	160	211	212	263	264
7175	572	537	539	512	526	497	498	469	475	467
74	546	532	537	506	537	493	493	463	477	467
72	546	529	550	517	546	510	511	485	488	482

	315	316	367	368	419	420	471	472	523	524
7175	437	410	420	433	367	318	197	193		368
74	438	415	455	445	413	400	377	366		329
72	461	442	487	487	453	443	408	420		387

Remove from Oven

	524
7175	323
74	313
72	373



Section #III Index

Acid Oxalic 5610-08
" Succinic 5670-18, 6018-16
Alcohol Amb. 5962-60
" & Hyposulphite soda 5727-24
Ammonia 5379-77
" Carbonate 5415-31

Barium Sulphite 6038-36
Barley 5491-89

Calcium Carbonate 5915-13
Cerium " 5826-23
Corn Starch 5577-74
5451-79, 5486-84

Ferric Hydroxide 7070-68
Ferrous " 5977-75

Glass Powd. Lead 5585-83

Hydrogen Peroxide 5243-41

Kaolin 5865-63

Magnesium Carbonate 5860-58
Mica 5696-94

Nickels Boiled in 1% KOH 5969-67

Nickels Green Hydrate Ppt. 2 1/2 5263-61

Potassium Antimonate 5582-7
7168-66. 7175-72
" Formate 5616-14
" Sample with out Barium treatment 5325-23
" Selenate 5591-89
" Stick by Lime 5238-37
" Sulphide 5993-91. 5996-94
6001-5999. 6006-04. 6013-11
" Tellurate 5595-93

Strontium Carbonate 5522-20

Sulphur 6053-51. 6056-54
6063-61. 6066-64

Additions to Section II

The following cards have been added to Section II



25 B A pricked from old endurance
cell # 25 B after 1501 runs treated
as per # 2271 J.W.A.

Endurance

	568	569	620	621	622	623	774	775		776
25 B	283	248	264	267	217	240	163	172	3 cells not pricked out	229

	577
25 B	251


9343.- Pocket from old cell #27
titrated according to # 22-85 JWA
Run reg in 21% KOH
9343
59 60 111 112 163 164 215 216
9343 231 253 288 290 203 217 177 175
367 368
9243 245 263
Bad curve.


9304 Pocket from old endurance cell #27 treated as per # 2281 J.W.A.
9304 0 177 245 246 332 378 388 402 410 417
9304 422
Endurance
9304 283 330 307 319 203 217 153 187
9304 350 272

13032	Three req mix 3.2 cake
01	crimped @ 100 Conv @ 150
00	Treated as per # 13032 JWH.

9302	mixed wrong	433	500	505	512	518	518	522	522	
01	520 mixed	532	532	540	542	548	552	553	556	
00	wrong	327	500	501	506	512	511	513	513	

9302	523	523								
01	552	547								
00	518	512								

Endurance

	62	63	114	115	166	167	267	269		
9302	545	543	547	542	560	553	503	515	3 hrs 210 RPM	
01	58	577	568	562	550	573	478	500	Mixer	
00	532	528	532	533	536	532	517	505		

	370	371								
9302	548	538								
01	573	577								
00	553	547								

Calipers

	Original	After 1st Run	Before Endurance
8550	90-101-99		
49	94-103-103		
48	93-104-104		

8550 Group of 3 reg 'ins in clamps
49 for Endurance 3.2 gun ins 3390
48

@ 500

8550	467	633	737	706	736	308	333	747	722	736
49	477	587	673	642	675	267	292	658	653	655
48	497	617	700	662	709	294	300	687	689	692

8550	728	706	732	730						
49	667	643	669	668						
48	707	674	697	708						

Endurance

	65	66	117	118	169	170	221	222		273
8550	650	52	472	570	510	550	390	383	Bore Mic	300
49	526	52	442	575	400	400	210	203	Bore Mic	190
48	700	667	552	662	583	588	333	323	Bore Mic	258

	344									
8550	313									
49	187									
48	260									

Calipers

	Original	after 1st Run	Before Endurance
8547	90-101-100		
46	89-100-101		
45	91-101-105		

8547 Group of 3 Reg Mix in clamps for
46 Endurance 3.2 gpm in 21°C
45

@500

8547	508	515	552	529	533	408	417	515	524	532	
46	515	520	535	530	533	467	475	533	586	533	
45	510	518	543	542	547	458	483	537	542	542	

8547	525	521	545	520							
46	527	522	583	529							
45	526	522	538	527							

Endurance

	65	66	117	118	169	170	221	222	273	274	323
8547	494	481	462	470	433	477	423	393	Shut off 10:04 April 2		467
46	520	487	467	482	495	500	500	447			437
45	497	486	463	483	428	478	417	417			492

	324										
8547	453										
46	440										
45	477										

	Original	after 1st run		167th run
92.99	104-104-107			112-110
98	102 101-100			109-10
97	104-105-105			113-111

Note - 92.97 is brim voltage also.

92.99 Three Reg his 312 gum
98 smooth press 100 Corrug 150
97 Treated accordingly @ 2280 gwa.

92.99	542	549	547	547	548	552	554	553	552	548
98	560	556	550	546	547	552	550	550	547	543
97	565	563	562	551	553	560	557	558	554	553

92.99	547									
98	543									
97	555									

Endurance

	62	63	114	115	166	167	268	269		370
92.99	547	544	525	533	530	540	497	485	530	530
98	538	533	517	520	527	537	467	477	495	495
97	549	545	532	533	530	527	533	533	523	523

	371									
92.99	513									
98	466									
97	533									